

Please cite the Published Version

Uddin, Mohammad Abbas, Rahman, Md Mahbubor, Haque, Abu Naser Md Ahsanul, Smriti, Shamima Akter, Datta, Eshita, Farzana, Nawshin, Chowdhury, Sutapa, Haider, Julfikar ¹ and Muhammad Sayem, Abu Sadat ¹ (2022) Textile colouration with natural colourants: a review. Journal of Cleaner Production, 349. p. 131489. ISSN 0959-6526

DOI: https://doi.org/10.1016/j.jclepro.2022.131489

Publisher: Elsevier

Version: Accepted Version

Downloaded from: https://e-space.mmu.ac.uk/629405/

(cc) BY-NC-ND

Usage rights: tive Works 4.0 Creative Commons: Attribution-Noncommercial-No Deriva-

Additional Information: This is an Author Accepted Manuscript of an article published in the Journal of Cleaner Production by Elsevier.

Enquiries:

If you have questions about this document, contact openresearch@mmu.ac.uk. Please include the URL of the record in e-space. If you believe that your, or a third party's rights have been compromised through this document please see our Take Down policy (available from https://www.mmu.ac.uk/library/using-the-library/policies-and-guidelines) https://www.sciencedirect.com/science/article/pii/S0959652622011106

Textile Colouration with Natural Colourants : A Review

Mohammad Abbas Uddin¹, Md. Mahbubor Rahman¹, Abu Naser Md Ahsanul Haque², Shamima Akter Smriti¹, Eshita Datta³, Nawshin Farzana⁴, Sutapa Chowdhury¹, Julfikar Haider⁵ and Abu Sadat Muhammad Sayem^{6,*}

¹Bangladesh University of Textiles Dhaka, Bangladesh ²Deakin University, Institute for Frontier Materials, Waurn Ponds, VIC 3216, Australia ³Bangladesh University of Business and Technology, Dhaka, Bangladesh ⁴Daffodil International University, Dhaka, Bangladesh ⁵Department of Engineering, Manchester Metropolitan University, M1 5GD, UK ⁶Manchester Fashion Institute, Manchester Metropolitan University, M15 6BG, UK

*Corresponding Author:

Abu Sadat Muhammad Sayem, Manchester Fashion Institute Manchester Metropolitan University, Righton Building, Cavendish Street, Manchester, M15 6BG, UK Tel: +44 (0)161 247 2673 E-mail: <u>asm.sayem@mmu.ac.uk</u>

Abstract

This paper provides an in-depth review of the natural colourants covering their classifications, sources, extraction techniques, application techniques in relation to different textile fibres and their advantages and challenges. The academic readers will find here an overview of the latest developments in extraction and application techniques of a variety of natural colourants. Almost all commercially produced natural fibres and the major synthetic fibres are found to be dyeable and printable with natural colourants. Although the production of natural colourants offers a lot of environmental benefits, their application techniques in textile colouration are not always sound for environment due to the need of synthetic mordants in colouration process. Advances in modern agriculture and biotechnology can play a key role in sorting the limitations of natural colourants and at the same time more and more investigations are still required to establish their cleaner application on textiles.

Keywords

Natural colourants, textiles, fibres, extraction process, dyeing, printing

1. Introduction

Nature is superbly colourful and is an abundant source of colourants. Both living and nonliving members of nature store an unending amount of colouring substances, including both dyestuff and pigments, in their constituents. The mankind, have mastered extracting and using those since the dawn of human civilisation (Zerin et al., 2019). These colourants have been used in the food, cosmetics, and pharmacology and textiles since time immemorial (Saxena and Raja, 2014; Sen et al., 2019). Soon after the arrival of synthetic dyes in 1856, the use of natural colouranta in the textile industry had started to decline (Samanta and Agarwal, 2009). The practice of using natural dyes has only survived in the cottage industry sector by artisans, enthusiasts, and small entrepreneurs. Nevertheless, the vast application of synthetic dyes in textile colouration is causing alarming environmental pollution and harm to aquatic ecosystem as these are produced from petrochemical sources, which bear potentially carcinogenic and toxic compounds (Chavan, 2013; Hassaan and El Nemr, 2017). This has again geared up the interest in natural colourants among the environmentally conscious consumers.

A brief summary of recent scientific research works on the application and sustainability of natural colourants in textile substrates with important observations are revealed in this paper.

2. Classification of Natural colourants for textiles

Natural colourants can be classified in multiple of ways broadly depending on their hues, sources, chemical structures and their applications (Gulrajani et al., 1995; Mansour, 2018; Patel, 2011; Shahid et al., 2013; Teli et al., 2000; Yusuf et al., 2017b). They can be classified as *'substantive colourants*,' which can be directly applied to the textiles, such as indigo, turmeric and *'adjective colourants*,' which need mordant to apply to materials, such as logwood (Samanta and Konar, 2011).

2.1. Classification based on hue

The Colour Index, known as CI number, jointly published by the Society of Dyers and Colourists (SDC) based in the UK and the American Association of Textile Chemists and

Colorists (AATCC), classify colourants based on their application classes and chemical constitutions. Natural colourants have been grouped separately in volume 3 of the SDC Colour Index that includes 32 natural reds, 6 natural oranges, 4 natural blues, 5 natural greens, 29 natural yellows, 12 natural browns, 6 natural blacks, and one natural white in the list (Saxena and Raja, 2014) (see Table 1).

CI Natural	Number of Dyes	Percentage (%)	Examples of sources	Reference
Yellow	29	30.4	Barberry (Berberis aristata), tesu flowers (Butea monosperma), safflower yellow (Carthamus tinctorius L.), kamala (Mallotus philippensis), dyer's chamomile (Anthemis tinctoria), turmeric (Curcuma longa)	(Ahmed, 2009; Biertmpfel and Wurl, 2009; Teli et al., 2001, 2000)
Orange	6	6.5	Annatto (Bixa Orellana)	(Adeel et al., 2019; Gupta and Gulrajani, 1994)
Red	32	34.8	Madder (<i>Rubia tinctorum</i>), manjistha (<i>Rubia cordifolia</i>), brazil wood/sappanwood (<i>Caesalpinea</i> <i>sappan</i>), morinda (<i>Morinda citrifolia</i>), cochineal (<i>Dactylopius coccus</i>) and lac <i>Coccus laccae</i>)	(Ahmed, 2009; Biertmpfel and Wurl, 2009; Vankar, 2000; Yusuf et al., 2017b)
Blue	4	3.3	Natural indigo (<i>Indigofera</i> species), Kumbh (Manipur) and the flowers of Japanese 'Tsuykusa'	(Adeel et al., 2019; Ahmed, 2009; Yusuf et al., 2017b)
Green	5	5.5	Usually very rare, other than a combination of woad/indigo with indigo dyes	
Brown	12	13	Virtually unlimited source. Cutch is an ancient brown dye sourced from the wood of acacia trees. Lady's mantle (<i>Alchemilla vulgaris</i> <i>L</i> .), Milfoil (<i>Achillea millefolium L</i> .), Wild marjoram (<i>Origanum vulgare L</i> .)	(Biertmpfel and Wurl, 2009; Hao et al., 2006; Yusuf et al., 2017b)
Black	6	6.5	Roots of iris plant, lac, carbon, and caramel	(Gulrajani et al., 1995; Hao et al., 2006; Yusuf et al., 2017b)

Table 1. Number of natural dyes in each hue registered in Colour

2.2. Classification based on sources

Four out of the five kingdoms of living things - animals (all multicellular animals), plants (all green plants), fungi (moulds, mushrooms, yeast) and prokaryotes (bacteria, blue-green algae) – are known to be the sources of extractable colourants. Among the non-living things, soil and rocks provide readily usable colourants. Based on the origin, natural dyes can be obtained primarily from three sources: plants, minerals, and animals (Chakraborty, 2014; Patel, 2011), as shown in Figure 1. These are discussed below.



Figure 1. Broad classification of natural dyes based on sources

2.2.1. Dyes derived from Plants

Historically the majority of the natural dyes are obtained from the plants as various parts of several plants such as roots, leaves, twigs, seeds, bark, fruits, rinds, husks, stems, hulls, trunks etc. are found to be potentially rich in colourants (Chakraborty, 2014; Saxena and Raja, 2014; Yusuf et al., 2017b). Some plants can produce different colours in different body parts (see Table 2) depending on their age, surrounding environmnet and the growth conditions and the season of the year (Hancock and Boxworth, 1997). In India, around four hundred fifty dye-yielding plants have been identified (Gulrajani et al., 1995; Yusuf et al., 2017b).

Table 2. Natural dyes obtained from different parts of different plants

Botanical name	Common name of the plant	Part used	Hue	Reference
Eupatorium	Siam weeds	Whole plant	Yellow	(Vijaykumar and Kumar,

odoratum				1999)
Ageratum conyzoides	Goat weed	Whole plant	Yellow	(Vijaykumar and Kumar, 1999)
Atrocarpus heterophyllus	Jackfruit tree	Bark	Yellow	(AK and P, 2007)
Delonix regia	Gulmohar	Flower	Olive green	(Saxena and Raja, 2014)
Tectona grandis	Teak	Leaves	Yellow	(Saxena and Raja, 2014)
Acacia nilotica	Babool	Leaves, bark	Yellow/brown	(Chattopadhyay et al., 2013)
Nymphaea alba	Water lilly	Rhizomes	Blue	(Saxena and Raja, 2014)
Dahlia variabilis	Dahlia	Flowers	Orange	(Saxena and Raja, 2014)
Emblica officinalis	Amla	Bark, fruit	Grey	(Saxena and Raja, 2014)
Ziziphus mauritiana	Indian Jujube Ber	Leaf	Pink	(Saxena and Raja, 2014)
Moringa pterygosperma	Drumstick	Leaf	Yellow	(Saxena and Raja, 2014)
<i>Tamarix aphylla</i> <i>L</i> . Karst	Tarfa/Athl	Leaf	Brown	(Baaka et al., 2017)
Brassica oleracea L. var. capitata f. rubra	Red Cabbage	Leaf	Red	(Haddar et al., 2018)
Tamarindus indica	Tamarind	Leaves, seeds	Yellow, brown	(Saxena and Raja, 2014)
Rumex maritmus	Golden dock	Seeds	Brown	(Savvidis et al., 2017)
Eucalyptus camaldulensis	Eucalyptus	Bark	Yellow and brown	(Biertmpfel and Wurl, 2009; Mongkholrattanasit et al., 2009; Naz and Bhatti, 2011)
Pterocarpus santalinus	Red sandal wood	Wood	Red	(Gulrajani et al., 2003; Savvidis et al., 2017)
<i>Acacia catechu</i> wild	-	Bark	Reddish Brown	
Bougainvillea glabra	-	Flower	Yellow/Brown/Green / Orange	(Patil et al., 2012)
Hibiscus	-	Flower	Red/pink/brown/violet	
Jatropha curcas	-	Bark/leaves/root	Blue/Yellow	
Indigofera tinctoria	-	Leaves, pods	Blue	
Melastoma Malabathricum	-	Fruits, Flowers	Purple/Black	
Rubia cordifolia	-	Whole plant	Red-brown	
Terminalia	-	Root, seeds,	Dark Blue/Yellow,	
chebula Toong herenduc		truit, Bark	Gray Vellow brown	
100na nexanara	-	r towers/seeds	i enow-brown	

2.2.2. Dyes derived from the Mineral origin

Few earth pigments composed of inorganic metal salts and metal oxides are known to be applicable as textile colourants. Some vital mineral colourants are cinnabar (a toxic mercury sulfide mineral), chrome yellow, iron buff, mineral khaki and manganese brown, malachite, ultramarine blue, azurite, gypsum, talc, charcoal black (Chakraborty, 2014; Saxena and Raja, 2014). Mineral colours are water insoluble inorganic compounds, which are precipitated onto the fibre by a process known as double decomposition (Affat, 2021; Cavalcanti et al., 2021; Choudhury, 2018; Patel, 2011; Samanta and Konar, 2011).

2.2.3. Dyes derived from Animals

Few insects and molluses contain extractable colourants in their bodies. Colourants carminic acid, kermesic acid and accaic acid originate from the dried bodies of insects - cochineal, kermes and lac respectively (Yusuf et al., 2017a). Cochineal (*Dactylopius coccus*) is a scale insect, and the bodies of female cochineals and their eggs contain carminic acid (C.I. Natural Red 4), which has found applications in food colouration, drug and textile dyeing. This colourant produces a varity of shades of pink, crimson red, scarlet red, and blue onto natural fibres when used with different mordants (Adeel et al., 2018). Kermes (*Kermes vermilio*) is another scale insect, and like cochineal, the bodies of female kermes and their eggs contain colouring substances. This insect is the source of a yellowish-red dye kermesic acid (C.I. Natural Red 3). Kermess powders were used for textile dyeing in ancient England, France, Spain, Turkey, and Scotland. Another red dye C.I. Natural Red 25, is obtained from the resinous secretion of different species of lac insects – *Laccifer lacca* and *kerria lacca*.

The historic dyes Tyrian purple and Tekhtelet blue are obtained from sea snails belonging to *Bolinus brandaris* (also known as *Murex brandaris*), *Hexaplex trunculus* (i.e. *Murex trunculus*) and *Stramonita haemastoma*.

2.2.4. Colourants from Fungi

Different non-mycotoxigenic species of soil and wood-inhabiting fungi produce dyes and pigments, which have potential applications in the food, pharmaceutical, cosmetics and textile industries. In some cases, such colourants exhibit very high fastness to light and washing when applied in textiles. Soil inhabiting filamentous fungus *Monascus purpureus, Isaria farinosa, Emericella nidulans, Fusarium verticillioides,* and *Penicillium purpurogenum* produce red, pink, red and yellow shades on cotton substrates when dyes in the presence of alum and ferrous sulfate (Velmurugan et al., 2010, 2009). Wood inhabiting fungi *Penicillium murcianum* and *Talaromyces australis* can yield yellow and red respectively on wool (Hernández et al., 2019). Other wood-staining fungi *Chlorociboria aeruginosa, Scytalidiumcuboideum,* and *S. ganodermophthorum* produce green, red, and yellow pigments suitable for dyeing cotton, polyamide 6.6, polyester, polyacrylic, and wool materials (Weber et al., 2014).

2.2.5. Colourants from Microbes

Interestingly different species of bacteria can produce pigments. For example, the *Rhodobacter sphaeroides, Flavobacterium multivorum, Agrobacterium aurantiacum, Gordonia jacobea, Paracoccus carotinifaciens*, and *Sphingomonas* sp. make carotenoid, a class of organic pigments with yellow-orange-red hues, in their bodies (Mumtaz et al., 2019).

2.3. Classification based on chemistry

Chemistry-based classification of natural colourants identifies the particular chemical groups with specific characteristic properties exist in their chemical structures (Yusuf et al., 2017a). Based on major chemical constituents present, they are grouped as indigoids, quinonoids, flavonoids, carotenoids, tannin based dyes (Choudhury, 2017; Kumar and Sinha, 2004; Saxena and Raja, 2014). Figure 2 shows a schematic of the above-mentioned structures of natural dyes with examples.



Figure 2. Natural dyes of different chemical structure and respective plant sources

2.3.1. Indigoid dyes

Examples of natural dyes containing indigoids are given in Table 3. Indigo is the most common dye of this group, and its main chemical ingredient is indigotin (CI Natural Blue 1, C.I. number 75780) found in the leaves of Indigo plants. The structure is very similar to synthetic indigo (C. I. Vat Blue1, C.I. 73000). Still, natural indigo contains some red dye indirubin, which can generate a prominent reddish tone to the textile materials (Saxena and Raja, 2014). The most widely used source are Indigofera species, Isatis species, and Polygonum species. The Indifofera is known to give about 60% of yield of indigo dyes (Clark et al., 1993). The other most crucial dye in this class is the Tyrian purple that can be derived from the Mediterranean mollusks of the genera - Purpura and Murex. As it is shown in the Figure 3, it is basically the 6, 6' dibromo derivative of indigo (Figure 3) including indirubin, monobromoindirubin, 6,6'-dibromoindirubin and indigotin (Mantzouris and Karapanagiotis, 2014; Vasileiadou et al., 2019, 2016). This natural source is no longer used as the shellfish

became extinct as a large number was needed to produce even a tiny amount of dyes (Daniels, 2006; Patel, 2011).

Common	Commonly available species	Active ingredient	Reference
name			
Indigo	Indigofera species such as I.	Mainly Indigotin with	(Patel, 2011;
	tinctoria, I. errecta, and I.	indirubin	Saxena and Raja,
	sumatrana; pala indigo (Wrightia		2014)
	tinctoria), Assam indigo		
	(Strobilanthes flaccidifolius),	glucoside indican or	
		isatan B including some	
	Japanese knotweed (Polygonum	indirubin and kaempferol	
	tinctorium) and common knotweed		
	(P. aviculare), Nerium tinctorium,		
	Marsdenia and Lonchocarpus		
	cyanescens		
Woad	Isatis tinctoria and other species	Indigotin	
Tyrian	molluscs Murex trunculus, M.	6,6'-dibromoindigo also	
purple	brandaris and Purpura lapillus	indirubin and	
^ ^		monobromoindirubin	

Table 3. Naturally available indigoid dyes



Figure 3. Chemical Structure of indigo and tyrian purple (Patel, 2011)

2.3.2. Quinonoid dyes

Quinonoids are the most diverse naturally occurring colouring substances. The colour gamut is widely distributed, ranging from yellow to red. Further classification of these dyes based on chemical structure includes the classes of anthraquinones, α -naphthoquinones, and benzoquinones (Bechtold, 2009).

(a) Anthraquinone dyes:

A majority of the red dyes belong to anthraquinone structure (see Figure 4). They come from both plants and insects (Table 4). The most famous natural dye is the alizarin (1, 2-dihydroxy anthraquinone) obtained from the European madder (*Rubia tinctorum*). There is also Indian madder, known as manjishta/manjeet (*Rubia cordifolia*), known for its health benefits in Ayurveda. The composition of extracted anthraquinone differs from plant to plant. The main composition of Indian madder is purpurin (1,2,4-trihydroxyanthraquinone) (Gupta et al., 2001). Madder roots are known to be a source of more than 35 anthraquinoids (Schweppe, 1993). Rhubarb, another anthraquinone dye, has been known for its pharmaceutical values for over 400 years. These plants grow in Himalayas in India, China and Tibet, Siberia, and Europe (Khan et al., 2012). The dye (CI Natural Yellow 23) is extracted from the roots and contains a complex mixture of anthraquinones (Bechtold, 2009; Schweppe, 1993). Other dyes include lac, morinda, and cochineal. These dyes are known to have good colour fastness to wash and light (Chakraborty, 2014; Saxena and Raja, 2014).

Dye name	CI Number	CI name	Natural sources	Reference
Alizarin	75330	Natural red 6, 8, 9, 10, 11, 12	Madder, chayroot	
Purpuroxanthin or xanthopurpurin	75340	Natural red 8, 16	Madder, munjeet	
rubuadin	75350	Natural red 8, 16	madder, <i>Gallium</i>	
morindanigrin	75360	Natural Red 19	Morinda umbellata	
munjistin or purpurinxanthin- carboxylic acid	75370	Natural Red 16,8	madder, munjeet	
Morindadiol	75380	Natural red 18	Morinda root	(Hancock
Soranjidiol	75390	Natural red 18	Morinda root	and
chrysophanic acid	75400	Natural Red 23	turkey rhubarb	Boxworth, 1997; Vasileiadou
Purpurin	75410	Natural red 16, 8	Munjeet, madder	et al., 2019)
Pseudopurpurin	75420	Natural red 14, 9, 8	Gallium, madder	
morindon	75430	Natural Red 19, Yellow 13	oungkouda	
emodin or frangulaemodin	75440	Natural Green 2, Yellow 14	Persian berries	
Laccaic acid	75450	Natural red 25	Coccus laccae (Lac dye)	
Kermesic acid	75460	Natural red 3	K. licis	
Carminic acid or cochineal	75470	Natural red 4	C. cacti	

Table 4. Some anthraquinone dyes with CI number and source



Figure 4. Structures of some anthraquinone dyes (Patel, 2011)

(b) Naphthoquinone dyes:

Like anthraquinone dyes, naphthoquinones also give away different shades of orange, red, or reddish-brown hues (Saxena and Raja, 2014). The two most prominent members of this class are lawson (2-hydroxy-1,4-naphthoquinone) and juglone (5-hydroxy-1,4, naphthoquinone) (see Figure 5). The commonly known henna (*Lawsonia inermis* L.), cultivated and used in Bangladesh, India, Northern and Eastern Africa, and Australia is the prime source of lawson (Cartwright-Jones, 2006; Chakraborty, 2014) for the traditional use of colouring hair and nails, also in dyeing wool and silk in orange to brown colours (Obara and Onodera, 1979) directly or in combination with different mordants (Agarwal et al., 1992). Henna can also be used to dye polyester with better affinity than polyamide (Gupta and Gulrajani, 1994). Another naphthoquinone, Juglon, is available in plenty in different parts of nut trees

(*Juglandaceae*) depending on the variety of trees. The main component of juglone is a glycoside, e.g. 5-hydroxynaphthohydroquinone-4-b-D-glycoside (Schweppe, 1993).



Figure 5. Chemical structure of henna (2-hydroxy-1,4-naphthoquinone) and juglon (5-hydroxy-1, 4-naphthoquinone)

(c) Benzoquinone dyes

This dye range is relatively small. The most important dye is the red dye found in safflower (*Carthamus tinctorius* L., CI Natural Red 26), known as Carthamin (see Figure 6). The dye structure is quite complex and sensitive to hydrolysis (Obara and Onodera, 1979). The oxidation of yellow cartharmin produces the red-orange dye to produce carthamon. Safflower is cultivated in subtropical regions of Egypt, Iran, India, China, Africa, North and South America from ancient times for food, cosmetics, pharmaceuticals, and colouration of wool, silk, and cotton (Oda, 2001). Mushrooms and lichens are also known to be source of Benzoquinone dyes (Bechtold, 2009).



Figure 6. Structure of carthamin (Bechtold, 2009)

2.3.3. Flavonoid dyes

Flavonoid dyes consist of the largest colour palette ranging from pale to deep yellow, orange to reds and blues through plant sources (Markham, 1982). These dyes are derivatives of phenylalanine and the acetate coenzyme A esters, which possess a C6-C3-C6 structure (Guinot et al., 2006). The plant uses flavonoids as a defence mechanism and signalling

compounds for reproduction, symbiosis, and pathogenesis. These can substantially absorb UV-B light and thus can prevent damage of leaf tissues by UV radiation. These compounds are produced in large quantities in the plant and substantially affect soil composition during decomposition. The role of flavonoids as a food content has been extensively studied due to their antioxidant properties, anti-ulcer and anti-viral infections, and prevention of chronic age-related diseases, including cardiovascular disease and cancer (Cook and Samman, 1996; D. Li et al., 2019; Perez-Vizcaino and Fraga, 2018). An average human diet, based on an estimation, includes a flavonoid intake ranging between 100 and 1000 mg/day (Aherne and O'Brien, 2002). Approximately 6000 naturally occurring flavonoids, most of which are pale, yellow or colourless, are known to have been isolated from different plants (Wätjen et al., 2005). Figure 7 presents the chemical structures of common flavonoids.



Figure 7. Structure of a) flavonol (pale yellow) b) flavone and c) anthocyanidin (Orange to violet) (Giusti and Wallace, 2009; Gulrajani and Gupta, 1992; Patel, 2011)

2.3.4. Carotenoid dyes

These are red, orange or yellow pigments that are commonly seen in the most photosynthesising organisms. Around 750 different carotenoids (not including cis-trans isomers) have so far been separated from different natural sources (Britton et al., 2004). Most carotenoids are xanthophylls and carotenes and are responsible for attractive colours in many red and yellow fruits and vegetables, the feather of birds such as flamingos and wild cock. Carotenoids also occur in algae, fungi, yeasts, moulds, mushrooms, and bacteria. All the sources of orange pigment have shared standard structural features such as polyisoprenoid structure and a series of centrally located bonds (Chakraborty, 2014; Chandrika, 2009). The basic carotenoid structure is linear and symmetrical, containing around 40 carbon atoms with one or two cyclic structures at the end of their conjugated chains. The long alternating single and double bonds systems give distinct molecular shapes, light-absorbing properties, and

chemical reactivity (Chandrika, 2009). Two unique type of carotenoids that are commonly used for textile colourtaion are Saffron (*Crocus stativus*) and annatto seeds (*Bixa Orellana*). Crocetin, the yellow pigment is the main colourant in saffron flowers, while bixin and norbixin are the main colourant for annatto seeds (Chandrika, 2009; Saxena and Raja, 2014). Other dye in this class also includes Indian mahogany (*Cedrela toona*) and harshingar (*Nyctanthes arbor-tistis*) flowers.



Figure 8. Structures of some carotenoid dyes (Patel, 2011)

2.3.5. Tannin-based dyes

Tannins are chemically polyphenolic compounds having molecular weights between 500 and 3000 and are water-soluble. Tannins are obtained from the various parts of the plants, such as fruit, pods, plant galls, leaves, bark, wood, and roots (Saxena and Raja, 2014; Yusuf et al., 2017b). The colour ranges are from light yellow to light brown, which contributes to food

and beverages. Tannins are capable of precipitating proteins (Hagerman et al., 1997). They are usually classified into three groups-hydrolysable (gallotannins and ellagitannins, derived from fustic, oak, waterlilies etc.), condensed tannins (proanthocyanidins and derived from oak, willow bark, cutch and waterlilies etc.) and the phlorotannins (Giusti and Wallace, 2009). Tannins improve the affinity towards natural dyes by working as a natural mordant for textile dyeing (Mussak and Bechtold, 2009), and essential ingredients to produce yellow, brown grey, and black colours (Gulrajani, 2001).

2.4. Classification based on application methods

Based on the method of applications in textile colouration, natural colourants can be classified into two distinct groups: substantive and non-substantive. Substantive colourants do not require any pretreatment of the fabric before dyeing, such as indigo, orchil, and turmeric. On the other hand nonsubstantative colourants require a chemical, called mordant, to increase between colourants and fibre.

Most natural dyes are nonsubstantive. The dyes that are capable of formation of complex with metal mordants also called mordant dyes (Yusuf et al., 2017b). Unlike animal fibres, mordant plays a significant role for the dyeing of vegetable fibres such as cotton, which does not have carboxylic acid or amino group to provide attachment sites for reaction (Saxena and Raja, 2014). With the same source of dyes, different mordants produce different shades or colours with different hues or tones (Abdel-Kareem, 2012; Yusuf et al., 2017b). Mordants can come from natural sources such as pomegranate peel (*Punica granatum* L), gallnut (*Quercus infectoria* L) and catechu (*Acacia catechu*) or can be synthetic (Shahid-ul-Islam et al., 2019). Possible use of biomordants cited in different literature is given in (İşmal, 2017). Monogenetic dyes produces only one colour with mordants, whereas polygenetic dyes produce different colour based on the mordant used in the dyeing process (e.g., logwood, alizarin, fustic and cochineal) (Choudhury, 2017). Mordant dyes are mostly limited to wool, which provides deep shades with excellent wash and light fastness when applied with metallic mordants. Mordant dyes contant ligands (OH, H₂, COOH), which helps to form a stable, coordination complex inside the wool fibre (Baaka et al., 2017).

Mordants are classified to three groups, which are metallic, oil mordants, and tannins (Saxena and Raja, 2014). Metal salts of aluminum, tin, chromium, copper, and iron are commonly

used in traditional textile dyeing. Chromium are black listed due to environmental concern, and copper is also in restricted category with certain limits, while the presence of tin in wastewater is a challenge. Alum (in the form of basic aluminium sulphate) or potash alum (double sulphate of potassium and aluminium) is the most widely used aluminium mordant, which as high as 10–20 % of alum can be used on the weight of the material can be used in textile dyeing (Saxena and Raja, 2014). Iron sulphate and copper sulphate are used as mordant in textile materials. Oil mordants are mainly used in dyeing processes using madder to produce Turkey red colour, which forms a complex with alum (Patel, 2011). On the other hand, tannic acid or tannins are first choice of mordants for cotton and cellulosic fibres and are important to produce yellow, brown, grey and black colours with natural dyes (Patel, 2011).

Unlike mordant dyes, extracted dyes from natural sources can be of direct, acid, cationic, vat dye (Patel, 2011; Saxena and Raja, 2014) and disperse dye in nature (Yusuf, Shabbir and Mohammad, 2017, Chattopadhyay, 2011). These dyes can be applied in exhaust and continuous/semi-continuous method. In exhaust dyeing technique, the dyes are transfered from dyebath into the fibre polymer by adsorption and absorption and finally get fixed into polymer network. On the other hand, padding (mostly pad-dry-cure in natural dyeing) has some distinct advantages over exhaust method (Maulik et al., 2011; Syamili et al., 2012).

3. Advancement in Dye Extraction Processes

The amount of colourants present in natural sources are very limited. They need specific extraction technique to separate dye-bearing components from their original sources (Gupta, 2019). Elimination of non-colourant components like carbohydrate, protein, and chlorophyll is vital in extracting colouring substances from natural sources to get pure colourants. There are various methods of extracting dye-bearing materials from natural sources, as shown in Figure 9.



Figure 9. Various Extraction processes of natural colourants (Mansour, 2018)

Natural dyes can also be extracted using the acidic or alkaline aqueous medium. The dyes containing a phenolic group in their structures are appropriate for alkaline extraction. In addition, the extraction of lac dye and red dye from saffron can also be done by the acid/alkaline method (Gupta, 2019). The aqueous extraction process usually takes a long time; in that case, the microwave-assisted extraction process can be useful. It is reported that the liquor from Coleus atropurpureus leaves containing tannin and flavonoid can be extracted at an optimized condition of temperature 100°C, microwave power of 400 watts, and an M: L ratio of 0.001g/mL (Selfina Gala, 2018). Ultrasound, a good source of energy, can make the extraction process even faster. A comparative analysis on using the dye extracts by traditional and ultrasound method is observed in a work, where 0.5 %, 1 %, 2 % stock extracts were obtained from 0.5 g, 1 g, 2 g of dye fine particles in 100 ml water and extracted in the ultrasound sonicator at 35 KHz frequency for varying time. Here harda and tamarind seed coats were used as a natural mordant, and turmeric, henna was used to dye wool fabric. The ultrasound method gives effective extraction and higher colour value for both natural colourants and mordants than the simple aqueous method (Javed Sheikh, 2016). Another well-known and cost-effective process is fermentation where the bio enzymes help to extract dye bearing compounds. Various enzymes like cellulase, pectinase can be used for this purpose. Indigo can be extracted by the fermentation process. (Gupta, 2019) . The dyes extraction process from Nila leaves is optimized by the maceration method in work. 12-hour

of maceration at pH 11 is found to be the most optimal process to get a sharp blue shade from Nila leaves. The maceration method generates sharper dye than the boiling method in cotton material. (Lisna Hidayati, 2018).

4. Development in Colouration Techniques with natural colourants

As natural dyes are mostly non-substantive, it is challenging to reproduce shades and to standardise a recipe and it requires a skilled artistry. Almost all of the natural dyes require the use of mordants to get fixed into textile substrates (Samanta et al., 2016). The factors that influence textile colouration with natural dyes are pH, ionic strength of dyebath, molecular size of dyes, and dyebath temperature (Vankar, 2017; Ben et al., 2021). The following subsections highlights the recent adavncements in colouration of different fibre types with natural colourants.

4.1. Dyeing and printing of Cotton

Cotton is widely investigated as the most frequently used natural fibre to explore its suitability in dyeing with a range of natural dyes (El-Sayed et al., 2022; Kavyashree, 2020; Yıldırım et al., 2020). Several studies are unfolding the kinetic modelling of different natural dyes on cotton. In a recent study, kinetic experiments of curcumin (dye sourced from turmeric rhizome) on cotton showed a strong affinity between dye and cotton. The dyeing process followed the pseudo-second-order model, and the whole process was reported exothermic (A. N. M. Haque et al., 2018). Moreover, the value of enthalpy was matched in chemisorption mechanism, which suggests the possible chemical interaction of curcumin with cotton. Similar results were found with lac dye (Chairat et al., 2008). Furthermore, similar findings were reported when lac dye was used on chitosan pre-treated cotton, and curcumin was used on regenerated cellulose such as modal (Ahsanul Haque et al., 2018; Rattanaphani et al., 2007). Hence, a certain interaction between cotton and a range of natural dyes are well established as a favourable condition for dyeing. However, one of the critical problems with natural dyes is the low fastness properties, which might be due to their heterogeneity and often limits their application (Kasiri and Safapour, 2014). To offset this problem, several advanced dyeing techniques have been developed over the years to enhance the applicability of natural dyes and make the dyeing process environmentally more

sustainable. Table 5 lists the research works on cotton and other fibres with different natural dyes in various methods.

Source of Natural Clourant	Fibre dyed	Mordant	Mordanting and Dyeing process	Reference
African marigold (<i>Tagetes erecta</i>	Cotton	Alum, ferrous sulphate, copper sulphate.	 Pre-mordanted for 30 min, at 80°C, m:l 1:40, 2% mordant, rinsed, sqeezed, dried; cotton is dyed at aquous dye extract, m:l 1:40; silk sample is dyed at pH 4 with sodium acetate and acetic 	(Jothi, 2008)
	Silk	stannous chloride	 acid buffer; washed in cold water and dried at room temperature, dipped in saltwater for dye fixing. 	
	Cotton		- cotton is dyed for 60 min, 80°C, m:l 1:25 with Glauber's	
Bacteria (Serratia sakuensis)	Silk	_	- silk and wool are dyed using acid dyeing method for 60 min,	(Vaidyanathan et al., 2012)
	Wool		- cold washed with non-ionic detergent and air dryed.	
Gulzuba flower	Cotton	Alum, ferrous sulphate, copper	 Pre-mordanted for 30 min, 60°C, m:l 1:50; rinsed, squeezed, dried; cotton sample is dyed with dye extract at m:l 1:40, 60 min; 	
(Hibiscus mutabilis)	Silk	stannous chloride,	- silk sample is dyed at pH 4 by adding a buffer solution (sodium acetate and acetic	(Shanker and Vankar, 2007)
	Wool	dichromate, stannic chloride	 acid), m:l 1:40, 60min; washed with cold water and dried at room temperature; dipped in brine for dye fixing. 	
Lac insect (Luccifer lacca)	Cotton	-	- dyed at pH 3, m:l 1:100, varying time 5 min, 60 mim, 120 min, at different temperature 10°C, 30°C, and 60°C	(Chairat et al., 2008)
Mangosteen hulls (<i>Garcinia</i> mangostana	Cotton	Ferrous sulphate, calcium	 Cotton and silk are dyed for 60 min at 60°C, m:l 1:25; Post-mordanted by 	(Chairat et al., 2007)

Table 5. Major studies on cotton, silk and wool with natural dyes

Linn)		hydroxide,	impregnating in mordant solution at room temperature for	
	Silk	Alum, zinc tetrafluorob orate	30 min, - washed with water and air- dried.	
Senna Tora	Cotton	Ferrous sulphate, Copper sulphate, Zinc sulphate,	- both cotton and silk were pre- mordanted with any mordant for 60 min at 40°C, m:11:100.	(Lee and Kim,
(Cassia tora L.)	Silk	Manganese sulphate, aluminium sulphate Nickel sulphate	- both are dyed for 60 min at 60°C, m:l 1:100	2004)
Turmeric rhizome (<i>Curcuma longa</i>)	Silk	Ferrous sulphate	 pre-mordanted with 0.5 g/L FeSO₄ for 10 min, at 70 °C, m:l 1:20; dyed for 100 min at different temperatures (70°C, 85°C, 100°C), pH 7, m:l 1:20; hot washed with water at 80°C, then cold wash at room temperature, squeezed, dried for 10 min at 60°C. 	(A. N. M. Haque et al., 2018)
Turmeric rhizome (<i>Curcuma longa</i>)	Cotton	Ferrous sulphate, aluminium sulphate, zinc chloride, tannin	 Pre-mordanted for 10 min at room temperature, m:l 1:40; dried for 5 min at 130°C; dyed for 60 min at at 60°C, m:l 1:40; rinsed with warm and cold deionised water, air dried 	(Mulec and Gorjanc, 2015)
Pomegranate (<i>Punica</i> granatum) and Tea leaf (<i>Camellia</i> sinensis)	Cotton	-	 acrylamide monomer was padden on cotton fabric pre- soaked with K₂S₂O₈, dried at 95°C for 5 min and cured at 140°C for 5 min; dyed for 60 min at 90°C, m:1 1:50, pH 4.2 ± 0.2; washed with non-ionic detergent for 10 min at 60°C, then cold-washed and dried. 	(Maulik et al., 2011)
Lac insect (Luccifer lacca)	Cotton	-	- cotton pretreated with chitosan was dyed for 180 min at 30°C, pH 3.0, m:l 1:100;	(Rattanaphani et al., 2007)

Green tea leaf (Camellia sinensis)	Cotton	-	 Ethanol extract of green teal leaf mixed with 8% citric acid is applied on cotton by pad-dry- cure at 50°C, m:l 1:20, 3psi, 100% wet pick up; air dried and cured for 3 min at 140°C 	(Syamili et al., 2012)	
Henna leaves (<i>Lawsonia</i> <i>inermis</i>)	Cotton	copper sulphate	 UV irradiation of dye powder and cotton fabric for 60 min, pre-mordanted with 4% copper sulphate for 120 min at 65°C, dyed in presence of 3% NaCl for 120 min at 65°C 	(Iqbal et al., 2008)	
Lac insect (Luccifer lacca)	Cotton	-	- cationised cotton fabric was dyed for 60 min at 80°C, pH 2.5. m:l 1:40, sonic power (100- 500W)	(Kamel et al., 2007)	
	Cotton	stannous chloride, stannic chloride,	- Cotton was pretreated with 2% tannic acid for 4-5 hours and then pre-mordanted with any one mordant for 60 min at 40° C;		
Dom sheng (Symplocos spicata)	Silk	ferrous sulphate, copper	- Silk and wool were pre- mordanted without tannin acid treatment,	(Vankar et al., 2008a) (a)	
	Wool	and potassium dichromate	dyed in sonicator process for 60 min at pH 5.09, 30-40° C, varying m:1 1:10 to1:40		
D 1 ·	Cotton	alum, ferrous sulphate, stannic	- Cotton was pre-treated with 2% tannic acid an dthem pre- mordanted with 1-2% mordant (any one).		
Berberine (Mahonia napaulensis DC)	Silk	stannous chloride,	- silk and wool fabrics were directly pre-mordanted - all fabrics were individually	(Vankar et al., 2008a) (b)	
	wool	copper sulphate, potassium dichromate.	dyed for 180 min at 30-40°C without sonicator and for 60 min at 30-40°C with sonicator		
Catechu (<i>Acacia</i> <i>catechu</i>) and Tectona (<i>Tecton</i> <i>a grandis</i>)	Cotton	Ferrous sulphate, alum, copper sulphate, potassium dichromate, stannous chloride, stannic chloride	 enzyme treated cotton fabric was pre-mordnated with 2% mordant solution of for 30 mins at 45°C; dyed at sonicator bath for 60 min at 45°C, m:l 1:30 	(Vankar and Shanker, 2008)	

Red cabbage (Brassica oleracea)	Cotton	-	 cationised for 60 min at 50°C, dried at room temperature; dyed by ultrasonic energy for 60 min at 80°C, pH 9 	(Ticha et al., 2016)
Onion (Allium cepa)	Cotton		 microwave plasma treated cotton was dyed in onion pulp juice and skin etraction separately for varying time 10 - 30 min at 70°C 	(Chen and Chang, 2007)
Pomegranate (Punica granatum)	Cotton	-	 Pre-treated with plasma and chitosan dyed for 60 min at 100°C, pH 7 	(Haji, 2017)
Red Calico leaves (Alternanthera bettzikana)	Cotton	-	 cotton and calico leaves were gamma irradiated, dyed for 60 min at 60°C, m:l 1:30, varying pH 5-10 	(Khan et al., 2014)
Note: m:l = mater	ial to lique	or ratio		•

Chemical pre-treatment of cotton (apart from conventional mordanting) before dyeing process is a common method for improving dye exhaustion and fastness properties of textiles. In a study with berberine, a significant increase in dye exhaustion on cotton together with very good colour fastness properties (washing fastness rating of 4 and dry cleaning fastness of 4-5) was achieved when the fabric was pre-treated with an anionic bridging agent containing dichloro-s-triazinyl reactive group (Kim et al., 2004). The bridging agent surpassed the weak interaction between cotton and berberine and therefore was able to provide good results. A few other chemicals like citric acid, hydrogen peroxide, chitosan also reportedly has a better influence on the dyeability and durability of cotton when the colouration was performed with green tea leaf, curcumin, and lac, respectively (Ammayappan and Moses, 2009; Rattanaphani et al., 2007; Syamili et al., 2012).

More advanced technologies like sonication, UV irradiation, and gamma-ray radiation are also introduced to enhance dyeability from natural dyes. Several studies using the sonication method reported notable improvement in dyeing performance. This method is also called sonicator dyeing (ultrasound-assisted dyeing), which has attracted researchers in recent years due to its known profile of providing greater dye yield in a reduced amount of electrolyte, dyeing time and temperature (Kamel et al., 2007). In a study with lac dye on cotton, the ultrasonic technique was found to have increased the dye uptake around 66% increase compared to the conventional method (Kamel et al., 2007). In a relevant study, the efficiency of dyeing was found to increase about 7-9% when cotton was dyed with eclipta dye using the sonication method instead of the conventional method (Vankar et al., 2007). Along with the dye uptake property, the fastness characteristics of dyed fabric was also found to improve by using sonicator dyeing on cotton with *Symplocos spicata* (Vankar et al., 2008b). However, it should be noted that in all these cases, chemical pre-treatment, cationization or enzyme treatment was required before the sonication (Ghorpade et al., 2000; Senthilkumar et al., 2002; Ticha et al., 2016; Vankar and Shanker, 2008).

Among the other techniques, UV irradiation of both dye and cotton was found effective for increasing colour strength with henna dye (Iqbal et al., 2008). The irradiation helped the colouring component in henna leaf (lawsone) to be degraded hydrolytically and produce bigger spaces inside cellulose structure, which synergistically resulted in a high exhaustion property of the dye onto cotton (Iqbal et al., 2008). Besides, gamma-ray radiation on both natural dye and cotton before the dyeing step was reported as an efficient technique not only because it can reduce the amount of mordants required for the process but also can boost the colour fastness (Khan et al., 2014).

The plasma treatment of fabric surface before dyeing is reported while dyeing cotton with natural dye. This, in fact, is a non-destructive modification of fabric surface which influences the dye exhaustion properties. A report on onion dye on cotton revealed a significant increase in cotton fabric hydrophilicity after plasma treatment, ceasing the necessity of using metallic salt as a mordant (Chen and Chang, 2007).

Apart from dyeing, a few studies on printing on cotton with natural dyes, i.e., alkanet, rhubarb, henna, and curcumin. Naturally sourced thickener such as meypro gum was found helpful to achieve better colour strength than commonly used synthetic thickeners in pigment printing technique (Rungruangkitkrai and Mongkholrattanasit, 2012). Application of binders instead of mordanting agent was also proved effective in case of pigment printing. Additionally, mercerized cotton showed better printability with natural dye as well as displayed higher colour efficiency (Bahtiyari et al., 2017). In case of screen printing guar gum was used as thickener. Moreover, Antibacterial property of printed cotton with natural dyes was also studied by researchers (Teli et al., 2013). They applied functional biopolymer chitosan as eco-friendly mordant with different concentration on cotton fabric before printing

with natural dyes like catechu, turmeric, marigold. The chitosan mordanted printed samples were found to have good colour values as well as excellent antibacterial activity, which openned a new door for eco-friendly printing with antibacterial finishing of textiles. The colour-fastness of printed cotton was reported between 4 and 5 for alkanet and rhubarb dyes (Rekaby et al., 2009). Besides, several natural dyes sourced from, i.e., turmeric, indigo, pomegranate, henna were reported in the literature to become successfully printed on cotton fabric in different methods, including resist printing and screen printing and having good fastness properties (Hakeim et al., 2005; Hebeish et al., 2006; Karolia and Buch, 2008). At present digital printing with water based ink-jet inks is gaining popularity arund the world and offers benefits over conventional printing methods. In a recent study, a novel ecofriendly process was offered to investigate the potential application of four natural natural pigments (annatto, cutch, pomegranate fruit rind, and golden dock) for the preparation of water-based ink-jet inks for digital printing on cotton fabric (Savvidis et al., 2014). Colour consistency and fastness results of printed samples after fixation were promising and this paves the way of developing suitable eco-friendly inks using natural dyes for the digital printing of cotton.

4.2. Dyeing and printing of wool

Different natural dyes from various natural sources like Iranian and Indian madder, Gulzuba, Lac, Anthraquinone, Rutin, Weld, Tea, Walnut bark, Marigold etc. used for dyeing and printing of wool are reported. Different types of mordants and methods of mordanting techniques significantly affect the rate of fading and colour fastness property. (Shanker and Vankar, 2007) has reported that pretreating with 2 to 4% metal mordants and maintaining a material to liquor ratio of 1:40 is optimal to obtain very good fastness properties for wool, silk and cotton samples (see Table 5). A study conducted by (Gong et al., 2020) has shown the impacts of different natural mordants like pomegranate peel, citric acid, Arjun bark, chlorophyll extract etc. and the metal mordants like sodium dichromate, stannous chloride, copper sulfate, ferrous sulfate etc. on different fastness properties of wool fabrics dyed with 50% (on the weight of material) Cinnamomum camphora natural dye.

Low temperature plasma treatment is a water-free and clean process to modify the topography of of textile fibres. It can eliminate the hydrophobic nature and can pratly degarde the surface scales of wool fibre without affecting its bulk properties (Haji and Qavamnia,

2015; Zhang and Wang, 2015). Plasma treatment before dyeing is found to be very effective in increasing the dye and mordant penetration into the wool by increasing the -C=O groups and by removing the lipid layers on the surface of the fibres (Haji, 2020a, 2020b; Haji et al., 2016a, 2016b, 2014; Haji and Qavamnia, 2015).

The application of ultrasound is becoming a very useful technique for many chemical processes and reactions like chemical synthesis, fabric dying, water treatment, materials production etc. (Cravotto and Cintas, 2007). Comparison between conventional and ultrasonic dyeing processes for dye exhaustion of wool fabric using betanin dye was carried out, were characterized by mass techniques and fractional crystallization methods were applied to extract and isolate dyes from *Opuntia ficus-indica* plant (Guesmi et al., 2013). This study revealed that the dye exhaustion rating was improved from 30% to 60% by the sonication process within a shorter dyeing period. Another study showed that the dye extraction and the dye uptake percentage of wool fabrics with lac (*Kema lacca*) dye were increased by 41% and 47%, respectively, in the ultrasonic dyeing method than conventional process (Kamel et al., 2005).

Along with the dyeing of wool fabric with natural dyes, printing is also reported in different studies. Printing of wool fabric with henna (2-hydroxy-1,4-naphthoquinone) as the natural colourant is reported by (Hakeim et al., 2003), where different fixation techniques like steaming, microwave heating, thermofixation etc. were applied, and the influence of different printing conditions like thickening agent type, mordant type, glycerine concentration, pH value of printing paste, dye concentration etc. on the fastness properties and the colour strength of the printed wool fabric was studied.

4.3. Dyeing and printing of silk

Silk, one of the delicate natural fibres, is also well examined in dyeing with different natural dyes. It is a natural protein fibre that is prone to an alkaline environment like wool, especially when the pH value is over 9. Besides, silk persists cationic nature by an isoelectric point at pH 5 (Samanta and Konar, 2011). Due to this reason, dyeing on silk with natural dyes is preferably conducted at a slightly acidic condition (see Table 5) (Jothi, 2008). Curcumin, extracted from turmeric, was successfully used to dye silk at a range of temperatures between $60-100^{\circ}$ C using several mordants, e.g., FeSO₄, C₄H₆O₆, CuSO₄ (ANMA Haque et al., 2018).

It was well reported that mordanting of silk has a significant impact on the colour performance, brightness and fastness of dyed silk (Rungruangkitkrai and Mongkholrattanasit, 2012). However, among the metallic mordants, Ferrous sulphate was claimed to produce better results because of colour and fastness than other mordants (Chairat et al., 2007; Lee and Kim, 2004). A combination of two or more mordants was also found useful to achieve very good to excellent colour fastness properties (Pruthi et al., 2008).

Advanced dyeing methods are also reported for dyeing silk with natural dyes, like other major natural fibres (cotton, wool, etc.). Pre-treatment with enzymes, mainly lipase, diastase and protease–amylase before dyeing showed the enhancement in fastness property for dyed silk (Vankar and Shanker, 2009). Pre-mordanting followed by sonication was reported as an efficient method for silk to achieve better colour properties (Vankar et al., 2008b, 2008a). An increased dye diffusion was reported when silk fabric was treated with plasma before microwave-assisted dyeing (Dayioglu et al., 2015). Both the time and microwave energy in plasma treatment contribute in enhanced dye molecule diffusion into the silk polymer. In a different study, silk was dyed with natural dye with and without oxygen and argon plasma pre-treatment (Boonla and Saikrasun, 2013). The surface treatment enhanced the roughness of the silk surface, which resulted in higher adsorption capacity, especially for argon plasma treatment.

Apart from the silk dyeing approaches, there were a few attempts to print on silk fabric by natural dyes. A study of silk printing with alkanet and rhubarb colours reported the steam fixation method to be better than thermo-fixation in achieving higher colour strength (K/S value) (Rekaby et al., 2009). Besides, printing on silk fabric was also conducted using natural agents as thickeners like mango kernel gum and cassia seed gum, guar gum and a wide range of colours (varying mordant selection) and good fastness properties were reported (Babel and Gupta, 2016; Yadav et al., 2010).

4.4. Dyeing and printing of bast fibres

Bast fibres are obtained from the bast or outer cellular layers of the stems of various plants. They have found numerous applications in traditional and technical textiles. Their advantages include local supply chain, low price, environmental friendliness, satisfactory mechanical properties and recyclability.

4.4.1. <u>Jute fibre</u>

The golden fibre jute is a coarser variety of agro-renewable and eco-friendly natural fibre (Samanta et al., 2012, 2008). Most of the natural dyes applied on jute fibre are extracted from leaf, bark, wood, rind, seed, root, etc. Mordanting methods (pre, post, meta) and the types of mordant (bio or chemical) can change the depth of shade, dye uptake and fastness behaviour of jute fibre dyed with natural colourants. Pre-mordanting route favours dyeing of jute fabric with direct types of natural dyes in presence of chemical mordant aluminium sulphate (Samanta et al., 2003). In contrast, post-mordanting with chemical mordants exhibits good colour yield and fastness properties after the dyeing of bleached jute with annatto seeds (Chattopadhyay et al., 2014).

A notable number of research works has been carried out to determine the effect of biomordant (myrobolan) and eco-friendly chemical mordant with or without mordant assistant like metal salts such as ferrous sulphate, aluminium sulphate [Al₂(SO₄)₃.18H₂O], potash alum [K₂SO₄, Al(SO₄)₃.24H₂O] on bleached jute fabric (Samanta, 2018; Samanta et al., 2006; Samanta and Agarwal, 2007). The effect of mordant on bleached jute fibre has been analyzed by using single or double mordants Myrobolan, aluminium sulphate, ferrous sulphate, potassium aluminium sulphate, stannous chloride and EDTA at different concentrations and assessed the resultant variation in surface colour strength (K/S), colour difference and mechanical properties like breaking strength, breaking extension, bending length of bleached Jute fabric. Generally, the application of any kind of mordant irrespective of its application percentage or method causes loss in fabric strength with some increase in warp way breaking extension. The value of bending length dyed fabric is found to increase when mordanted with FeSO₄ or Al₂ (SO₄)₃ and to reduce to some extent when mordantedg with EDTA. Among all the mordants, highest colour strength (K/S) and colour differences value are found for a single application of FeSO₄ as mordant (without dyeing) on jute fabric as it is a transition metallic salt bearing an inherent colour. In the case of double mordanting, sequential treatment of Harda and FeSO₄ on bleached jute fabric exhibits high colour difference as Harda itself is a light yellow dye that adds additional colour tone on fabric (Samanta, 2018). Some major challenges in continuing the natural dyeing process on jute fabric are reproducibility of colour, dyeing variables, types, methods and concentration of mordant, fastness properties, dye uptake, etc.

Decorative look in jute fabric can be achieved by printing. However, there is hardly any research work found on the printing of jute with natural colourants. In one research, the ecofriendly chemically processed jute fabric is printed with natural dyes extracted from roots of *manjistha*, bark of *ratanjot* and seed of *Annatto* (particle size 400-800nm) by screen print method (Chattopadhyay and Pan, 2018). The printing paste constituted different natural resins like guar gum, gum arabic, sodium alginate, and gum indulka. Bio-scouring by mixed enzyme (cellulase and xylanase) and the non-ionic surface acting agent followed by bleaching was done to make jute fabric white, bright and soft and ultimately more suitable for printing. Myrobolan and potash alum both are applied separately and sequentially (double mordant) on bleached jute fabric. After dye extraction, the printing of jute fabric is done by the screen print method, where 20 to 40 mesh size screens exhibit better performance. After assessing all the printed fabrics, it was revealed that double mordanting jute fabric and application of guar gum as a thickener in print paste shows better colour yield and fastness characteristics on printing (Chattopadhyay and Pan, 2018).

4.4.2. <u>Flax fibre</u>

Among all bast fibres, flax fibre has fascinated the textile market because of its distinctive features such as high strength, smoothness, elegancy in appearance, quick moisture absorbency, rapid dryness, hygroscopicity, high air permeability, and comfortability. However, dye penetration in flax fibre becomes very difficult because of its high crystallinity in its cellulose structure. Few research works have been conducted on dyeing of flax fibre with natural dyes. Most cases, flax fabric, commonly known as linen, was dyed at boiling temperature (Grifoni et al., 2014; Sarkar and Seal, 2003; Wang et al., 2009). Potash alum is mostly applied for mordanting in all mordanting methods (pre, post and simultaneous) on linen fabric during dyeing with different natural dyes because of its ability to form coordinated complex and to chelate with natural dyes readily (Grifoni et al., 2014; Sarkar and Seal, 2003; Teli and Pandit, 2018). Bio-mordants such as Harda and Chestnut are also used for mordanting of flax fabric. Influence of mordants on colour yield, colour strength (K/S values) and other fastness properties of Sterculia foetida dyed linen fabric was analysed where bio(harda) mordanted linen fabric exhibits higher colour depth and good fastness properties than alum or without mordanted fabric both in pre and post mordanting method (Teli and Pandit, 2018). Moreover, Ultraviolet radiation properties of linen fabric can also be improved by the application of some natural dyes (extract from Helychrysum, Rubia, Daphne, Lavandula, Cynara, Chelidonium majus, *Sterculia foetida*) (El-Hennawi et al., 2017; Grifoni et al., 2014; Teli and Pandit, 2018).

4.4.3. Ramie, Hemp and Banana Fibres

Besides jute and flax, other bast fibres like ramie, hemp and banana are also known to the textile industry because their versatile applications expanded from luxurious clothing material to bio-composite.

The dyeing behaviour of Ramie fibre is influenced by its high crystalline structure, which thwarts the exertion of dyestuff into fibre molecules. Four natural dyes extracted from caesalpinia sappan, rhizoma coptidis, gardenia, and areca catechu contain brazilin, berberine, crocin, and crocetin and catechin colourants respectively have been applied on ramie fabric at 90°C for 50 to 70 min in neutral condition (Zheng et al., 2011). In this work, rare earth was employed as a metallic mordant in pre, meta and post mordanting method where post mordanting showed a high dye pickup percentage. Compared to other metallic mordants, rare earth metals increased fastness properties and stabilized colour shade at different p^H of naturally dyed ramie fabrics because of its formation of coordinated bond with natural dyes and fibre (Zheng et al., 2011). Ramie fabric was also dyed with curcumin in aqueous solution of NaOH/urea at low temperature without any use of mordant. The colour strength (K/S value) of ramie fabrics dyed in NaOH/urea solution found to have increased in compared to ramie fabrics dyed in water. This is because of the insertion of Na⁺ in the macromolecular structure of ramie fibre and swelling it, resulting in the decrease of fibre crystallinity and an increase of entrance of curcumin molecules into the cellulose macromolecules' space. It was also revealed that better colouration of dyed ramie fibre obtained at low temperature as hydration of cellulosic fibres by Na⁺ is an exothermic process and most of the curcumin decomposes in NaOH/urea aqueous solution at high temperature (S. Li et al., 2019).

Hemp fibre is known to the luxury textile industry, unlike flax and ramie. Fabric made from processed hemp fibre bears unique criteria such as proper ventilation, moisture absorbency, antimicrobial and anti-ultraviolet properties. Owing to higher strength and stiffness, it is also used in bio-composites. Hemp fibre's colour yield and colour fastness properties were found to be good, which makes it eligible for producing high value-added clothing. But very little

work has been found on the application of natural dyes on hemp fabric. This fibre was successfully dyed with a tannin-rich natural dye extracted from neem bark using water at 100°C for 60 min after pre-mordanted with AlK(SO₄)₂ (Inprasit et al., 2018). Neem dyed hemp fabric got an excellent rating in colour fastness properties as hydrophobic (aromatic) and hydrophilic (-OH) groups of polyphenol compound of tannin, hydrophilic(-OH) cellulose groups of hemp and AlK(SO₄)₂ mordant formed insoluble complex on hemp fabric surface which prevented leaching of dye molecule and preserve colour stability (Inprasit et al., 2018). Besides mordant, cationization process can also increase dye uptake and colour yield by changing ions on the fabric surface. Cationization on hemp fabric is applied during dyeing with the extract from Arabica coffee (Butthongkum et al., 2016).

Another most promising and eco-friendly bast fibre is banana fibre, which is collected from the pseudostem of banana plant and exhibits similar chemical properties to jute fibre. The study on application of natural dyes on banana fibre is very limited. Catechu extracted from the wood of acacia catechu can be applied on banana fibre without mordant or with different chemical mordants (alum, ferrous sulphate, stannous chloride). Experiments with banana fabric dyed at 90°C for 60 min in around neutral p^H and m:l 1:50 showed that mordanted banana fabric produced better colour depth after dyeing than without mordanting (Singh, 2020). Pre-mordanting method of dyeing revealed to be better in fastness properties as compared to post-mordanting and without mordanting. Banana fibre is also dyed with turmeric (Curcuma longa) via ultrasonic and conventional methods using various mordants (Canpolat et al., 2015). Ultrasonic methods revealed better colour yield than conventional dyeing technique, whereas Ferrous sulphate treated fabric gave better results than copper sulphate and alum.

4.5. Dyeing and printing of polyester

Polyester is systhetic fibre with higher tensile strength, better crease recovery and higher biological resistance in comparison to natural fibres (Edlund and Albertsson, 2003; Gulrajani et al., 2008). An attempt has been made by (Baig, 2011) in dyeing of polyester (PET) with natural indigo (*Indigofera tinctoria*) in exhaust method at different pH values. The outcomes of the study suggest that in the acidic pH range polyester fabrics could best be dyed, and hydrogen bonding was found as the key contributor to dye exhaustion into the polyester fabrics. Madder (*Rubia tinctorum*) is widely used for dyeing cotton, silk, wool etc. mainly,

but not typical for polyester dyeing. However, it was reported that dyeing 100% polyester fabric with madder at different temperatures ranging from 60 to 130°C along with five different natural mordants and seven different chemicals (Gedik et al., 2014).

A novel water-free and mordant free and resource-efficient dyeing of polyester fabric with natural colourant 'curcumin' in super-critical carbon dioxide (scCO2) is trialed by (Abate et al., 2019). The dyeing behaviour of polyester fabric with natural dyes is found to be more influenced by the system pressure than the dyeing temperature. To achieve the maximum colour strength and levelness, the mentioned dyeing parameters were 120°C, 25 MPa and 60 min. Walnut (Juglans regia) shells are also testified as a natural source of colour for polyester and polyester/viscose blended fabric dyeing (Eser et al., 2016). To improve dyeability and activate the polyester fibre, UV/ozone pre-treatment for 5 to 120 min is reported to apply prior to the dyeing procedure. The polyester fabric was dyed with Curcumin and saffron as a source of natural dye (Elnagar et al., 2014). Apart from the polyester dyeing approaches, there are several works on polyester fabric printing with natural dyestuffs. In a bio-technique approach, laccase enzyme was employed as an alternate of mordants to fix three different natural colourants, i.e. rutin, morin and quercetin, onto the polyester fabric (El-Hennawi et al., 2012). The laccase enzyme was reported to undergo enzymatic oxidative polymerization of the dyestuffs and helps achieve very good to excellent colour fastness. In another study, hiren alkanet (Root of alkanet plant) dye nanoparticles were reported to use for printing of polyester fabric by dye-printing technique and pigment-printing technique (Taha et al., 2020). Both the printing techniques were reported to provide very good to excellent fastness properties with higher colour strength. As a part of obtaining antimicrobial properties in printed polyester fabrics, chitosan biopolymer is reported to use in making a print paste with Curcuma tinctoria as a natural colourant and gelatinized starch (Abdou et al., 2013). The study reported that the use of chitosan helped to improve the dye uptake percentage of polyester fabric along with providing antimicrobial characteristics.

4.6. Dyeing and Printing of Nylon

Nylon is a synthetic fibre that contains amide groups in the polymer chain. Generally, acid dyes are used to colour nylon, but scientists are trying to apply vegetable dyes to nylon. It is reported that plant dyes like Turmeric and Rhubarb can be used to print nylon fabric using cellulase enzyme, which helps to extract the dye and besides this presence of benzyl alcohol or dimethylformamide in the printing paste quicken the dye diffusion in the fibre during steaming (Maamoun et al., 2007). Effect of different mordants on nylon is observed using onion, lac, and turmeric as natural colourants, where nylon was pre-mordanted at 100°C for 45 minutes, and the simple aqueous extraction process was used to extract colouring materials. Dyeing of nylon fabric was done in the open bath process, and high temperature high pressure (HTHP) process and all dyes give a good depth of shade at acidic conditions. Safflower, Madder, Curcumin, Saffron andRatanjot also provide good colour values and colour fastness properties on nylon using different mordants. Besides these plant dyes, liquid waste of Eucalyptus from lumber steaming also gives excellent wash fastness on nylon (Purwar, 2016).

4.7. Dye-fabric interactions and mordants

The interaction between natural colourants and textile fabrics can vary based on the chemical nature of the colourants and the types fibre. In cases where the dye molecules are water soluble and have a planer molecular structure and possessing conjugated bonds (such as turmeric, pomegranate, harda), and are substantive towards cellulose, they can directly be attached onto fabric at a high temperature (e.g., 100 °C), similar to the application of synthetic direct dyes (Samanta and Konar, 2011). However, some of the natural dyes possess either sulphonic or carboxylic groups that are more suitable for producing interconnection with the amino groups of wool or silk (such as saffron), while some dyes deliver cations (e.g., berberine) and produce covalent bonds with the carboxylic groups of protein fibres (Gupta, 2019). Several other natural dyes (such as indigo) are water insoluble and require transformation into water-soluble form by reduction reaction and then further oxidation onto the fabric during the final dyeing (Samanta and Konar, 2011). Nevertheless, natural dyes overall show a relatively low affinity (compared to synthetic dyes) towards textiles, and some of them have least or no affinity. As mentioned earlier in Section 2.4, often mordants are used to overcome this problem. Mordants produce a dye-mordant complex and thus enhance the affinity towards the fabric. This phenomenon not only results in a higher colour build-up, but also promotes a better colour fastness (Purwar, 2016). As the mordant, a number of tannins (such as hydrolysable and condensed) and metallic salts (such as ferrous sulphate, aluminum sulphate, zinc chloride) are frequently used. However, these synthetic mordants are at the end

responsible for polluting the effluent water, which lessens the greener prospect of using natural dyes.

4.8. Role of bio-mordants

Currently, a decent interest is growing on the use of bio-mordants that are sourced from completely natural origins. These mordants have already delivered promising results and comprehensive reports are already available in the literature. For example, a recent report from Habib et al. showed improved colour depth while using either zeera (Cuminum cyminum), harmal (Peganum harmala), illaichi (Elettaria cardamomum) or neem (Azadirachta indica) leaves extract as the mordant (Habib et al., 2021). In another study, turmeric (Curcuma longa) as a bio-mordant showed a higher colour strength (K/S 13.8) than synthetic mordants such as iron (K/S 2.09) during silk dyeing with coconut coir (Adeel et al., 2021). In a further report of silk dyeing, both the colour strength and fastness properties achieved by different natural mordants (such as individual extract of pomegranate, henna, acacia, rose or turmeric) were comparable with those achieved by using synthetic mordants (Adeel et al., 2020). Similar successes of using bio-mordants were also confirmed in case of protein-based natural dyes, such as cochineal (Amin et al., 2020). More encouragingly, a significant amount studies have validated the effective role of different bio-mordants in dyeing with natural dyes where a number of different dyeing techniques, such as common exhaustion method (Haji, 2010), microwave radiation (Zuber et al., 2019), ultrasonic treatment (Arifeen et al., 2021) and plasma treatment (Haji and Naebe, 2020) were used. Thus, the reported findings show the suitability and applicability of the bio-mordants in a varied range of application.

Table 6 Categories of synthetic and bio-mordants

Categories	Examples	Sustainability issues	Reference

Synthetic mordants	metallic salts such as sulfates (magnesium, aluminum, zinc, copper, cobalt, nickel, manganese or tin), chlorides (stannic, ferric, copper, zinc, aluminum and even neodymium or zirconium), hydroxides (calcium) and oxides (ferric or lanthanum)	Except alum and iron, most mordants are not environmentally safe and restricted by eco-certification. The generated effluent can cause water and soil contamination.	(İşmal, 2017; İşmal and Yıldırım, 2019; Rahman et al., 2013; Rovira et al., 2015; Shahid et al., 2013; Shahid and Mohammad, 2013; P S Vankar, 2017)
Biomordants	Vegetable tannin–containing substances such as myrobolan (Harda, <i>Terminalia chebula</i>), oak galls, sumac, or pomegranate rind, Zeera (<i>Cuminum Cyminum</i>), Harmal (<i>Peganum Harmala</i>), Illaichi (<i>Elettaria Cardamomum</i>) Neem (<i>Azadirachta Indica</i>) extract.	Environmentally alternative of synthetic mordants, however, colour performance and fastness are mostly unsatisfactory. In some cases, biomordants have therapeutic and ayurvedic properties.	(Cunningham et al., 2011; İşmal, 2017; Prabhu and Teli, 2014)

5. Functional treatments with natural colourants

Major chemical compounds found in natural dyes are indigoid, pyridine, carotenoid, quinonoid, flavonoids, betalains, anthocyanin, anthraquinone, and tannins provide several functional properties when applied on textiles. The interaction between these dyes and the functional groups (-OH, $-SO_3H$, -COOH, $-C_6H_5OH$, $-NH_2$) of different textile fibres can make a complex structure responsible for achieving such characteristics. A summary of natural dyes with a responsible chemical component for the specific functional property is presented in Table 7, but not discussed with further details in this section as it will go beyond the scope of this review.

Functional Property	Natural Dye with Botanic Name	Responsible component for functional properties	Substr ate tested with	Referen ces
Antimicrobial	Pomegranate peel (Punica granatum)	Hydrolysable tannins((pyrogallol)	Lyocell	(Rehman et al.,

Table 7. Natural dyes with the responsible chemical components for defined property

				2018)
Mosquito repellence	Pomegranate peel (Punica granatum) with different conc. of polyvinyl alcohol	 Ellagic tannin Polyvinyl alcohol	Cotton	(Rimpi and Archana, 2017)
Antimicrobial, Mothproofing property	Henna (Lawsonia inermis)	Lawsone (2-hydroxy- 1,4-naphthoquinone)	Wool	(Nazari, 2017; Yusuf et al., 2015)
Antibacterial and antioxidant	Chitosan treated Henna dyed (<i>Lawsonia inermis</i>)	Polysaccharide of (1-4)- linked D-glucosamine and N acetyl-D- glucosamine with its polycationic structure Lawsone (2-hydroxy- 1,4-naphthoquinone)	Jute	(Bhuiyan et al., 2017)
Antimicrobial	Chitosan treated tea(<u>Camellia</u> <u>sinensis</u>)	Polysaccharide of (1-4)- linked D-glucosamine and N acetyl-D- glucosamine with its polycationic structure. Polyphenol	Wool	(Shahid- ul-Islam, B.S. Butola, 2018)
Antibacterial	Bakayan (Melia Composita)	Alkaloids and limonoids	Silk, wool, Cotton	(Pal et al., 2016)
Antibacterial and UV protection	Madder(<i>Rubia</i> <i>tinctorum</i>)and Safflower (<i>Carthamus</i> <i>tinctorius</i>)	di-and tri hydroxyl anthraquinones and Carthamin respectively	Polyam ide 6	(Ibrahim et al., 2013)
Antibacterial	Neem (Melia azedarach)	Phenolic compounds and flavonoids	Hemp	(Inprasit et al., 2018)
Antimicrobial	Golden dock (Rumex maritimus) Indigo (Quercus infectoria)	Tannin	Wool	(Singh et al., 2005)
Antibacterial	Berberine (berberis vulgaris)	Berberine (a quaternary ammonium structure)	Wool	(Aminod din, 2012)
Antibacterial (but no activity against <i>Klebsiella</i> <i>pneumonia</i>)	Peony (Paeonia officinalis)	Paenol/paenoside/paeon olide/paenoniflorin	Cotton, Wool, Silk	(Lee et al., 2009)

Antimicrobial	 Goldthread (<i>coptis</i> <i>Chinensis</i>) Clove (<i>Syzygium</i> <i>aromaticum</i>) Gallnut Pomegranate 	 Alkaloid berberine Eugenol (2-methoxy-4 allyl-phenol) Penta-m-digalloyl-β- glucose, gallic acid Ellagic acid and tannin 	Cotton, Wool, Silk	(Lee et al., 2009)
UV protection, Antibacterial, Antioxidant	Modified Curcumin (<i>Curcuma Longa</i> <i>L.)by</i> reactive UV absorber	Curcumin react with oxalanilide and sulfatoethylsulfone group of UV absorber	Silk	(Zhou and Tang, 2016)
Mothproofing property	Walnut hull (<i>Juglans regia L.</i>)	Juglone (5-hydroxy- 1,4-naphthoquinone)	Wool	(Nazari, 2017)
Antibacterial, Antioxidant, Flame retardant, Waterproof	Dioscorea cirrhosa tuber	Condensed Tannins (proanthocyanidins)	Silk	(Yang et al., 2018)
Antibacterial, Antioxidant	Lycium ruthenicum Murray	Acylated Anthocyanins	Wool	(Dong et al., 2019)
Antimicrobial and UV Protection	Quercus infectoria and Acacia Catechu, Acacia nilotica, Kerria lacca, Mallotus philippinensis Rumex maritinus and Rubia cordifolia	Tannin	Cotton	(Gupta et al., 2005)
UV Protection	 Eucalyptus leaf extract (<i>Eucalyptus</i> camaldulensis) Orange Peel Blossoms of broom (<i>Cytisus</i> scoparius) Dandelion (<i>Taraxacum</i> officinale) 	 Tannin as major and flavonoids as minor Phenolic compounds (Narirutin and Hesperidin Flavonoids carotenoids 	Wool	(Hou et al., 2013; Křížová and Wiener, 2016; Mongkh olrattana sit et al., 2014)
UV Protection	Cannonball mangrove(<i>Xylocarpu</i> <i>s granatum</i>) bark extract.	Tannin	Cotton	(Pisitsak et al., 2016)
UV Protection	Flos Caryophyllata (clove) and acutissima shell	Tannin	Silk	(Cao et al., 2013)

UV Protection	Weld (Reseda luteola L.), Woad (Isatis tinctoria L.), Logwood(Haematox ylon campechianum L.), Lipstick tree (Bixa orellana L.), Madder(Rubia tinctoria L.),Brazil wood (Caesalpina brasiliensis L.)	Flavonoid	Hemp and Flax	(Grifoni et al., 2009)
UV Protection	Henna (<i>Lawsonia inermis</i>)	Lawson; 2-hydroxy- 1,4-naphthaquinone in Henna leaves	Cationi sed cotton	(Omer et al., 2015)
UV Protection	Turmeric(Curcuma longa)	Curcumin	Polyest er	(Sriumao um et al., 2014)
UV Protection	 Cochineal (Dactylopius Coccus costal) Weld (Reseda luteola) 	 Carminic acid (a large glucose units attached by anthraquinone moiety) Luteolin and some Apigenin 	Silk and Wool	(Gawish et al., 2016)
UV protection, deodorization, antimicrobial properties	 Gallnuts (Cynipidae) Areca nuts (Areca catechu L.) Pomegranate peels(Punica granatum L.) 	 Tannin (Gallnut tannin) Tannin (Catechuins and Epicatechuins) Pomegranate Tannin (Ellagic tannin) 	Silk	(Jung, 2016)
UV Protection and antibacterial	 Gromwell (Lithospermum erythrorhizon) Gallnut Banana Peel (Musa, cv. Cavendish 	 Deoxyshikonin Tannin Luteolin 	Cotton	(Hong et al., 2012; Salah, 2013)
AntiMoth	Silver oak, Walnut husk and Pomegranate rind	More than 40% tannin	Wool	(Shakya war et al., 2015)
Deodorizing	 Gardenia Coffee sludge <i>Cassia tora. L.</i> Pomegranate extract 	 Crocin Caffeine Antraquinones Ellagic acid 	Cotton, Silk, Wool	(Hwang et al., 2008)

Although natural dyes can improve the functional properties of textile materials, they are not free from limitations that demandn more research and development. The imparted functional properties like antimicrobial, antioxidant, antimoth or UV protection tend to decrease after several washing. So, more research should be done to enhance the stability of functional characteristics of natural dyes after laundering.

6. Advantages and challenges

Production of natural colourants encourages plantation, which can reduce CO_2 from the atmosphere and increase the level of O_2 in the atmosphere. Historically natural colourants were the primary colourants for textiles. Gradually synthetic colourants have grabbed the whole market of commercial textile colouration. Still, the associated industrial activities for producing synthetic colourants are harmful to the environment and climate. Time has come to move towards the natural colourants. Figure 10 represents the comparative positions of natural dyes over synthetic dyes. Increasing the plantation of colourant-bearing plant species can contribute to socio-economic benefits like poverty elevation through job creation, utilisation of barren lands, maintaining the fertility of arable lands through crop rotation, and greenhouse gas reduction. However, to achieve this, a range of technical, logistical and commercial challenges need to be overcome first (Zerin et al., 2019).



Figure 10. Comparative positions of natural colourants over synthetic colourants.

6.1 High volume production

Yield of the natural colourants is usually very low in their sources. Adopting non-traditional extraction methods such as ultrasonic, microwave and enzyme-assisted extraction (Samanta et al., 2018) and biotechnological interventions such as genetic engineering (Saxena and Raja, 2014) can improve the production rate and volume of natural colourants.

6.2 Consistency in colourants and colouration

As natural sources of colourants are not commercially produced at a large scale, proper grading and sorting of sources and colourants are not practised widely, like it is done for commercial crop production. As a result, the natural colourants available on the market nowadays are not consistent in quality, which results in inconsistent quality in coloured materials. This required a combined initiative from all stakeholders, including governments, farmers and industry leaders, to establish standard production and colouration processes and promoting them throughout the industry to get the true benefit of natural colourants.

6.3 Need of mordanting

As it is mentioned earlier, the non-substantive characteristic of natural colourants requires the use of mordants in colouration process. Synthetic mordants are responsible for generating harmful effluent. This is an area of improvement to popularise natural colourants. There have been plenty of research works on the extraction and application of natural colourants in the past. Now it is high time to concentrate on making the colouration process eco-safe too. Promoting the use of natural mordants and making them available fr the industry is a crucial challenge to meet.

6.4 Colour Fastness

Achieving high colour fastness to wash and light with natural colourants are sometimes difficult with or without mordants and it varies depending on the natural sources and types of mordant used (Samanta and Konar, 2011). As reported in section 2.4, mordants dyes usually impart deep shades with excellent wash and light fastness onto wool. However, cotton fibre seems to achieve low colour fastness to wash from natural colourants (see section 4.1). Pretreated of cotton with an anionic bridging agent containing dichloro-s-triazinyl reactive group was found to increase the colour fastness properties (washing fastness rating of 4 and drycleaning fastness of 4-5) when dyed with berberine (Kim et al., 2004). Sonicator dyeing on cotton with Symplocos spicata also can increase dye update and fastness properties in comparison to traditional exhaust dyeing (Vankar et al., 2008b). Gamma-ray radiation on both natural dye and cotton before the dyeing can boost the colour fastness (Khan et al., 2014). Pre-treatment of silk with lipase, diastase and protease-amylase enzymes before dyeing showed the enhancement in fastness property for dyed silk (Vankar and Shanker, 2009). Textile susbstrate dyed with marigold extract using iron and copper sulphate as mordant exhibit very good light and wash fastness at first instance but it starts to degrade after a few washes with soap (Jothi, 2008). On the other hand, wash and light fastness of dyed cotton, wool and silk fabric with dye extract from Serratia marcescens bacteria found to be low (grades 1 for light and 1-2 for washing) but the fastness against rubbing was found to satisfactory (grade 4–5 for silk and cotton and grade 3 for wool) (Vaidyanathan et al., 2012).

6.5 Price and effcieciny

Natural colourants usually have low yield, which ultimately increases the net cost of production (Zerin et al., 2019). Due to realively low deman and supply, their prices are also realively high when compared with their synthetic counterparts. The supply chain of natural colourants are not well established globally. In most cases they can be only sources locally in certain places and countries. This problem cannot be solved until any large volume production of natural colourants takes place. Consumers and textile professionals cannot solve this by themselves unless governmental policies and financing institutions supporting and promoting natural colourants do not come into existence.

Similarly the efficiency of colouration with natural colouranst is also not very notable. The efficiency in case of natiral colouranst depencts on the efficiency of the extraction process, the yield of colourants, efficiency of the dyeing process including use of ingredauents, water and energy and ultimate colour strength of textiles and fastness. There is hardly any literature that report the complete efficiency of colouration with natural colourants. However, innovations in extraction process and dyeing processes are said to be able to improve the efficiency of natural dye extraction, the ultimate yield, and dye update and colour strength (Zerin et al., 2019). For example, the use of ultrasonics in extraction and dyeing can save energy by reducing requirements of temperature and time, reduce pollution by decreasing the need to auxiliary chemical amd increasing due uptake and minimise the fibre damage, thus increases the overall efficiency through quality enhancement and lowering of processing cost (Shahid et al., 2013)

7 Conclusion

Natural colourants have a glorious past but a gloomy present in the textile industry. As the production of natural colourants promote plantation and the substances themselves are biodegradable, they attract a lot of sympathies from the environmentalists and show a lot of promise for future. But in fact, the efficiency of colouration with natural colouranst is not very much notable and the need of mordants result into the procution notorious effluent as well. The sections 3 and 4 indentified the innovations in extraction of natural colourants and dyeing processes with those colourants that can ensure higher yield and better quality in coloured textiles. At present, natural colourants are only surving with in cottage industries. To revive the glory of the natural colourants in textiles and enjoy true environmental benefits out of them, it is essential to have national and international policy support and financial investment to set up large scale production of colourants and colouration facilities with selected colourants, which are found to be more promising than others.

References

- Abate, M.T., Ferri, A., Guan, J., Chen, G., Nierstrasz, V., 2019. Colouration and bioactivation of polyester fabric with curcumin in supercritical CO2: Part I-Investigating colouration properties. J. Supercrit. Fluids 152, 104548.
- Abdel-Kareem, O., 2012. History of Dyes Used in Different Historical Periods of Egypt. Res. J. Text. Appar. 16, 79–92.
- Abdou, E.S., El-Hennawi, H.M., Ahmed, K.A., 2013. Preparation of novel chitosan-starch blends as thickening agent and their application in textile printing. J. Chem. 2013, 1-8.
- Adeel, S., Habib, N., Arif, S., ur Rehman, F., Azeem, M., Batool, F., Amin, N., 2020. Microwave-assisted eco-dyeing of bio mordanted silk fabric using cinnamon bark (Cinnamomum Verum) based yellow natural dye. Sustain. Chem. Pharm. 17, 100306.
- Adeel, S., Kiran, S., Shahid, M., Habib, S.R., Habib, N., Hussaan, M., 2021. Ecofriendly application of coconut coir (Cocos nucifera) extract for silk dyeing. Environ. Sci. Pollut. Res. 1–9.
- Adeel, S., Rafi, S., Mustaan, M.A., Salman, M., Ghaffar, A., 2018. Animal Based Natural Dyes: A Short Review. Handb. Renew. Mater. Color. Finish. 41–74.
- Adeel, S., Rehman, F.-U., Rafi, S., Zia, K.M., Zuber, M., 2019. Environmentally Friendly Plant-Based Natural Dyes: Extraction Methodology and Applications, in: Plant and Human Health, Volume 2. Springer International Publishing, Cham, pp. 383–415.
- Affat, S.S., 2021. Classifications, Advantages, Disadvantages, Toxicity Effects of Natural and Synthetic Dyes: A review. Univ. Thi-Qar J. Sci. 8, 130–135.
- Agarwal, A., Garg, A., Gupta, K.C., 1992. Development of suitable dyeing process for

dyeing of wool with natural dye henna (Lawsonia inerma). Colourage 39, 43-45.

- Aherne, S.A., O'Brien, N.M., 2002. Dietary flavonols: chemistry, food content, and metabolism. Nutrition 18, 75–81.
- Ahmed, H.E., 2009. History of Natural Dyes in North Africa 'Egypt,' in: Bechtold, T., Mussak, R. (Eds.), Handbook of Natural Colorants. John Wiley & Sons, Ltd, Chichester, UK, pp. 27–36.
- AK, S., P, A., 2007. Dyeing of jute and cotton fabrics using Jackfruit wood extract: Part I effects of mordanting and dyeing process variables on color yield and color fastness properties. Indian J. Fibre Text. Res. 32, 466–476.
- Amin, N., Adeel, S., Ahamd, T., Muneer, M., Haji, A., 2020. Sustainable application of cochineal-based anthraquinone dye for the coloration of bio-mordanted silk fabric. Environ. Sci. Pollut. Res. 27, 6851–6860.
- Aminoddin, H., 2012. Antibacterial dyeing of wool with natural cationic dye using metal mordants. Mater. Sci. 18, 267–270.
- Ammayappan, L., Moses, J.J., 2009. Study of antimicrobial activity of aloevera, chitosan, and curcumin on cotton, wool, and rabbit hair. Fibers Polym. 10, 161–166.
- Arifeen, W.-, Rehman, F.-U.-, Adeel, S., Zuber, M., Ahmad, M.N., Ahmad, T., 2021. Environmental friendly extraction of walnut bark-based juglone natural colorant for dyeing studies of wool fabric. Environ. Sci. Pollut. Res. 28, 49958–49966.
- Baaka, N., Mahfoudhi, A., Haddar, W., Mhenni, M.F., Mighri, Z., 2017. Green dyeing process of modified cotton fibres using natural dyes extracted from *Tamarix aphylla* (L.) Karst. leaves. Nat. Prod. Res. 31, 22–31.
- Babel, S., Gupta, R., 2016. Screen printing on silk fabric using natural dye and natural thickening agent. J Text. Sci Eng 6, 1-3.
- Bahtiyari, M.I., BENLİ, H., Yavaş, A., Candan, A., 2017. Use of different natural dye sources for printing of cotton fabrics. Text. Appar. 27, 259–265.
- Baig, G.A., 2011. Indigo dyeing of polyester (PET)-pH effects. J. Text. Inst. 102, 87-92.

- Bechtold, T., 2009. Natural Colorants– Quinoid, Naphthoquinoid and Anthraquinoid Dyes, in: Handbook of Natural Colorants. John Wiley & Sons, Ltd, Chichester, UK, pp. 151– 182.
- Bhuiyan, M.A.R., Islam, A., Islam, S., Hossain, A., Nahar, K., 2017. Improving dyeability and antibacterial activity of Lawsonia inermis L on jute fabrics by chitosan pretreatment. Text. Cloth. Sustain. 3, 1–10.
- Biertmpfel, A., Wurl, G., 2009. Dye Plants in Europe, in: Bechtold, T., Mussak, R. (Eds.), Handbook of Natural Colorants. John Wiley & Sons, Ltd, Chichester, UK, pp. 37–52.
- Boonla, K., Saikrasun, S., 2013. Influence of silk surface modification via plasma treatments on adsorption kinetics of lac dyeing on silk. Text. Res. J. 83, 288–297.
- Britton, G., Liaaen-Jensen, S., Pfander, H. (Eds.), 2004. Carotenoids handbook. Birkhäuser Basel, pp. 1-33.
- Butthongkum, S., Sritapunya, T., Mongkholrattanasit, R., 2016. Effect of cationization conditions on dyeing properties of hemp fabric with natural dye extracted from arabica coffee ground, in: Applied Mechanics and Materials. Trans Tech Publ, pp. 267–271.
- Canpolat, S., Merdan, N., Dayioglu, H., Koçak, D., 2015. Investigation of the dyeability behavior of banana fibers with natural dye extract obtained from turmeric plants. Marmara Fen Bilim. Derg. 27, 40–44.
- Cao, H.M., Yang, J.F., Zhu, G.Y., 2013. The performance of Flos Caryophyllata extract on black dyeing and UV resistance, in: Advanced Materials Research. Trans Tech Publ, pp. 564–568.

Cartwright-Jones, C., 2006. Developing guidelines on henna: a geographical approach.

- Cavalcanti, G.R.S., Rodrigues, F., Zhuang, G., Balme, S., Janot, J.-M., Fonseca, M.G., Jaber, M., 2021. Inorganic-organic hybrid pigments based on carminic acid and clay minerals. Dye. Pigment. 190, 109306.
- Chairat, M., Bremner, J.B., Chantrapromma, K., 2007. Dyeing of cotton and silk yarn with the extracted dye from the fruit hulls of mangosteen, Garcinia mangostana Linn. Fibers Polym. 8, 613–619.

- Chairat, M., Rattanaphani, S., Bremner, J.B., Rattanaphani, V., 2008. Adsorption kinetic study of lac dyeing on cotton. Dye. Pigment. 76, 435–439.
- Chakraborty, J.N., 2014. Fundamentals and practices in colouration of textiles, Second. ed. Woodhead Publishing India Pvt. Ltd, New Delhi.
- Chandrika, U.G., 2009. Carotenoid Dyes- Properties, in: Handbook of Natural Colorants. John Wiley & Sons, Ltd, Chichester, UK, pp. 221–236.
- Chattopadhyay, S.N., Pan, N.C., 2018. Ecofriendly printing of jute fabric with natural dyes and thickener. J. Nat. Fibers. 16, 1077-1088.
- Chattopadhyay, S.N., Pan, N.C., Roy, A.K., Khan, A., 2014. Dyeing of Jute Fabric with natural dye extracted from annatto. AATCC J. Res. 1, 20–27.
- Chattopadhyay, S.N., Pan, N.C., Roy, A.K., Saxena, S., Khan, A., 2013. Development of natural dyed jute fabric with improved colour yield and UV protection characteristics. J. Text. Inst. 104, 808–818.
- Chavan, R.B., 2013. Health and Environmental Hazards of Synthetic Dyes. Text. Rev. Mag. May.
- Chen, C., Chang, W.-Y., 2007. Antimicrobial activity of cotton fabric pretreated by microwave plasma and dyed with onion skin and onion pulp extractions, pp. 122-125.
- Choudhury, A.K.R., 2018. Eco-friendly dyes and dyeing. Adv. Mater. Technol. Environ. 2, 145–176.
- Choudhury, A.K.R., 2017. Sustainable chemical technologies for textile production, in: Sustainable Fibres and Textiles. Woodhead Publishing, pp. 267–322.
- Clark, R.J.H., Cooksey, C.J., Daniels, M.A.M., Withnall, R., 1993. Indigo, woad, and Tyrian Purple: important vat dyes from antiquity to the present. Endeavour 17, 191–199.
- Cook, N.C., Samman, S., 1996. Flavonoids—Chemistry, metabolism, cardioprotective effects, and dietary sources. J. Nutr. Biochem. 7, 66–76.
- Cravotto, G., Cintas, P., 2007. Forcing and controlling chemical reactions with ultrasound. Angew. Chemie Int. Ed. 46, 5476–5478.

- Cunningham, A.B., Maduarta, I.M., Howe, J., Ingram, W., Jansen, S., 2011. Hanging by a thread: natural metallic mordant processes in traditional Indonesian textiles 1. Econ. Bot. 65, 241–259.
- Daniels, V., 2006. The light-fastness of textiles dyed with 6,6'-dibromoindigotin (Tyrian purple). J. Photochem. Photobiol. A Chem. 184, 73–77.
- Dayioglu, H., Kut, D., Merdan, N., Canbolat, S., 2015. The effect of dyeing properties of fixing agent and plasma treatment on silk fabric dyed with natural dye extract obtained from Sambucus ebulus L. plant. Procedia-Social Behav. Sci. 195, 1609–1617.
- Dong, Y., Gu, J., Wang, P., Wen, H., 2019. Developed functionalization of wool fabric with extracts of Lycium ruthenicum Murray and potential application in healthy care textiles. Dye. Pigment. 163, 308–317.
- Edlund, U., Albertsson, A.-C., 2003. Polyesters based on diacid monomers. Adv. Drug Deliv. Rev. 55, 585–609.
- El-Hennawi, H.M., Ahmed, K.A., Abd El-Thalouth, I., 2012. A novel bio-technique using laccase enzyme in textile printing to fix natural dyes, pp. 245-249.
- El-Hennawi, H.M., Mahmoud, S.A., Ragheb, A.A., 2017. Eco-friendly coloration of silk and flax fabrics with natural dye enhanced by ultraviolet radiation. Egypt. Pharm. J. 16, 192.
- El-Sayed, E., Othman, H., Hassabo, A.G., 2022. A Short Observation on the Printing Cotton Fabric using Some Technique. J. Text. Color. Polym. Sci. 19, 17–24.
- Elnagar, K., Abou Elmaaty, T., Raouf, S., 2014. Dyeing of polyester and polyamide synthetic fabrics with natural dyes using ecofriendly technique. J. Text. 2014.
- Eser, F., Aktas, E., Onal, A., 2016. Dyeing quality of walnut shells on polyester and polyester/viscose blended fabrics. Indian J. Fibre Text. Res. 41, 188–194.
- Gawish, S.M., Farouk, R., Ramadan, A.M., Mashaly, H.M., Helmy, H.M., 2016. Eco-friendly multifunctional properties of cochineal and weld for simultaneous dyeing and finishing of proteinic fabrics. Int. J. Eng. Technol. 8, 2246–2253.
- Gedik, G., Avinc, O., Yavas, A., Khoddami, A., 2014. A novel eco-friendly colorant and

dyeing method for poly (ethylene terephthalate) substrate. Fibers Polym. 15, 261–272.

- Ghorpade, B., Darvekar, M., Vankar, P.S., 2000. Ecofriendly cotton dyeing with Sappan wood dye using ultrasound energy. Colourage 47, 27–30.
- Giusti, M.M., Wallace, T.C., 2009. Flavonoids as Natural Pigments, in: Handbook of Natural Colorants. John Wiley & Sons, Ltd, Chichester, UK, pp. 255–275.
- Gong, K., Rather, L.J., Zhou, Q., Wang, W., Li, Q., 2020. Natural dyeing of merino wool fibers with Cinnamomum camphora leaves extract with mordants of biological origin: a greener approach of textile coloration. J. Text. Inst. 111, 1038–1046.
- Grifoni, D., Bacci, L., Di Lonardo, S., Pinelli, P., Scardigli, A., Camilli, F., Sabatini, F., Zipoli, G., Romani, A., 2014. UV protective properties of cotton and flax fabrics dyed with multifunctional plant extracts. Dye. Pigment. 105, 89–96.
- Grifoni, D., Bacci, L., Zipoli, G., Carreras, G., Baronti, S., Sabatini, F., 2009. Laboratory and outdoor assessment of UV protection offered by flax and hemp fabrics dyed with natural dyes. Photochem. Photobiol. 85, 313–320.
- Guesmi, A., Ladhari, N., Hamadi, N. Ben, Msaddek, M., Sakli, F., 2013. First application of chlorophyll-a as biomordant: sonicator dyeing of wool with betanin dye. J. Clean. Prod. 39, 97–104.
- Guinot, P., Roge, A., Gargadennec, A., Garcia, M., Dupont, D., Lecoeur, E., Candelier, L., Andary, C., 2006. Dyeing plants screening: an approach to combine past heritage and present development. Color. Technol. 122, 93–101.
- Gulrajani, M.L., 2001. Present status of natural dyes. Indian J. Fibre Text. Res. 26, 191–201.
- Gulrajani, M.L., Bhaumik, S., Oppermann, W., Hardtmann, G., 2003. Dyeing of red sandal wood on wool and nylon, pp. 221-226.
- Gulrajani, M.L., Brahma, K.P., Kumar, P.S., Purwar, R., 2008. Application of silk sericin to polyester fabric. J. Appl. Polym. Sci. 109, 314–321.
- Gulrajani, M.L., Daga, R., Kapur, V., Agarwal, D., 1995. Studies on Dyeing of Silk with Different Classes of Dyes-Part II Black Dyes. Colourage 42, 37–41.

- Gulrajani, M.L., Gupta, D., 1992. Natural Dyes and Application to Textiles. Department of Textile Technology, Indian Institute of Technology, New Delhi.
- Gupta, D., Jain, A., Panwar, S., 2005. Anti-UV and anti-microbial properties of some natural dyes on cotton. Indian J. Fibre Text. Res. 30, 190.
- Gupta, D., Kumari, S., Gulrajani, M., 2001. Dyeing studies with hydroxyanthraquinones extracted from Indian madder. Part 1: Dyeing of nylon with purpurin. Color. Technol. 117, 328–332.
- Gupta, D.B., Gulrajani, M.L., 1994. Kinetic and thermodynamic studies on 2-hydroxy-1, 4-naphthoquinone (lawsone). J. Soc. Dye. Colour. 110, 112–115.
- Gupta, V.K., 2019. Fundamentals of Natural Dyes and Its Application on Textile Substrates,in: Chemistry and Technology of Natural and Synthetic Dyes and Pigments.IntechOpen.
- Habib, N., Adeel, S., Ali, F., Amin, N., Khan, S.R., 2021. Environmental friendly sustainable application of plant-based mordants for cotton dyeing using Arjun bark-based natural colorant. Environ. Sci. Pollut. Res. 1–7.
- Haddar, W., Ben Ticha, M., Meksi, N., Guesmi, A., 2018. Application of anthocyanins as natural dye extracted from *Brassica oleracea L. var. capitata f. rubra* : dyeing studies of wool and silk fibres. Nat. Prod. Res. 32, 141–148.
- Hagerman, A.E., Zhao, Y., Johnson, S., 1997. Methods for Determination of Condensed and Hydrolyzable Tannins. pp. 209–222.
- Haji, A., 2020a. Natural dyeing of wool with henna and yarrow enhanced by plasma treatment and optimized with response surface methodology. J. Text. Inst. 111, 467– 475.
- Haji, A., 2020b. Application of D-optimal design in the analysis and modelling of dyeing of plasma-treated wool with three natural dyes. Color. Technol. 136, 137–146.
- Haji, A., 2017. Improved natural dyeing of cotton by plasma treatment and chitosan coating; optimization by response surface methodology. Cellul. Chem. Technol. 51, 975–982.

- Haji, A., Amiri, Z., Qavamnia, S., 2014. Natural dyeing of wool with Arnebia euchroma optimized by plasma treatment and response surface methodology. J. Biodivers. Environ. Sci 5, 493–498.
- Haji, A., Mehrizi, M.K., Sharifzadeh, J., 2016a. Dyeing of wool with aqueous extract of cotton pods improved by plasma treatment and chitosan: optimization using response surface methodology. Fibers Polym. 17, 1480–1488.
- Haji, A., Naebe, M., 2020. Cleaner dyeing of textiles using plasma treatment and natural dyes: A review. J. Clean. Prod. 265, 121866.
- Haji, A., Qavamnia, S.S., 2015. Response surface methodology optimized dyeing of wool with cumin seeds extract improved with plasma treatment. Fibers Polym. 16, 46–53.
- Haji, A., Qavamnia, S.S., Bizhaem, F.K., 2016b. Optimization of oxygen plasma treatment to improve the dyeing of wool with grape leaves. Ind. Textila 67, 244–249.
- Haji, A.A.D., 2010. Functional dyeing of wool with natural dye extracted from Berberis vulgaris wood and Rumex hymenosepolus root as biomordant. Iran. J. of Chem. and Chem. Eng. 29, 55-60.
- Hakeim, O.A., Abou-Okeil, A., Abdou, L.A.W., Waly, A., 2005. The influence of chitosan and some of its depolymerized grades on natural color printing. J. Appl. Polym. Sci. 97, 559–563.
- Hakeim, O.A., Nassar, S.H., Haggag, K., 2003. Greener printing of natural colour using microwave fixation, 216-220.
- Hancock, M., Boxworth, A., 1997. Potential for colourants from plant sources in England and Wales. Cambridge.
- Hao, S., Wu, J., Huang, Y., Lin, J., 2006. Natural dyes as photosensitizers for dye-sensitized solar cell. Sol. Energy 80, 209–214.
- Haque, ANMA, Farzana, N., Smriti, S.A., Islam, M.A., 2018. Kinetics and thermodynamics of silk dyeing with turmeric extract. AATCC J. Res. 5, 8–14.
- Haque, Ahsanul, Md, A.N., Hussain, M., Smriti, S.A., Siddiqa, F., Farzana, N., 2018. Kinetic

Study of Curcumin on Modal Fabric. Tekstilec. 61, 27-32.

- Haque, A.N.M., Hussain, M., Siddiqa, F., Haque, M., Islam, G.M., 2018. Adsorption Kinetics of Curcumin on Cotton Fabric. Tekstilec. 61, 76-81.
- Hassaan, M.A., El Nemr, A., 2017. Health and environmental impacts of dyes: mini review. Am. J. Environ. Sci. Eng. 1, 64–67.
- Hebeish, A.A., Ragheb, A.A., Nassar, S.H., Allam, E.E., El Thalouth, J.I.A., 2006. Technological evaluation of reactive cyclodextrin in cotton printing with reactive and natural dyes. J. Appl. Polym. Sci. 102, 338–347.
- Hernández, V.A., Galleguillos, F., Thibaut, R., Müller, A., 2019. Fungal dyes for textile applications: testing of industrial conditions for wool fabrics dyeing. J. Text. Inst. 110, 61–66.
- Hong, K.H., Bae, J.H., Jin, S.R., Yang, J.S., 2012. Preparation and properties of multifunctionalized cotton fabrics treated by extracts of gromwell and gallnut. Cellulose 19, 507–515.
- Hou, X., Chen, X., Cheng, Y., Xu, H., Chen, L., Yang, Y., 2013. Dyeing and UV-protection properties of water extracts from orange peel. J. Clean. Prod. 52, 410–419.
- Hwang, E.-K., Lee, Y.-H., Kim, H.-D., 2008. Dyeing, fastness, and deodorizing properties of cotton, silk, and wool fabrics dyed with gardenia, coffee sludge, Cassia tora. L., and pomegranate extracts. Fibers Polym. 9, 334–340.
- Ibrahim, N.A., El-Zairy, W.M., El-Zairy, M.R., Ghazal, H.A., 2013. Enhancing the UVprotection and antibacterial properties of polyamide-6 fabric by natural dyeing. interactions 8, 9.
- Inprasit, T., Motina, K., Pisitsak, P., Chitichotpanya, P., 2018. Dyeability and antibacterial finishing of hemp fabric using natural bioactive neem extract. Fibers Polym. 19, 2121–2126.
- Iqbal, J., Bhatti, I.A., Adeel, S., 2008. Effect of UV radiation on dyeing of cotton fabric with extracts of henna leaves, 157-162.

- İşmal, Ö.E., 2017. Greener natural dyeing pathway using a by-product of olive oil; prina and biomordants. Fibers Polym. 18, 773–785.
- İşmal, Ö.E., Yıldırım, L., 2019. Metal mordants and biomordants, in: The Impact and Prospects of Green Chemistry for Textile Technology. Elsevier, pp. 57–82.
- Jothi, D., 2008. Extraction of natural dyes from African marigold flower (Tagetes erecta L) for textile coloration. AUTEX Res. J. 8, 49–53.
- Jung, J.S., 2016. Study of fastness, UV protection, deodorization and antimicrobial properties of silk fabrics dyed with the liquids extracted from the gallnuts, Areca nuts, and pomegranate peels, in: MATEC Web of Conferences. EDP Sciences, p. 3001.
- Kamel, M.M., El-Shishtawy, R.M., Youssef, B.M., Mashaly, H., 2007. Ultrasonic assisted dyeing. IV. Dyeing of cationised cotton with lac natural dye. Dye. Pigment. 73, 279– 284.
- Kamel, M.M., El-Shishtawy, R.M., Yussef, B.M., Mashaly, H., 2005. Ultrasonic assisted dyeing: III. Dyeing of wool with lac as a natural dye. Dye. Pigment. 65, 103–110.
- Karolia, A., Buch, H., 2008. Ajarkh, the resist printed fabric of Gujarat, pp. 93-97.
- Kasiri, M.B., Safapour, S., 2014. Natural dyes and antimicrobials for green treatment of textiles. Environ. Chem. Lett. 12, 1–13.
- Kavyashree, M., 2020. Printing of Textiles Using Natural Dyes: A Global Sustainable Approach, in: Chemistry and Technology of Natural and Synthetic Dyes and Pigments. IntechOpen.
- Khan, A.A., Iqbal, N., Adeel, S., Azeem, M., Batool, F., Bhatti, I.A., 2014. Extraction of natural dye from red calico leaves: Gamma ray assisted improvements in colour strength and fastness properties. Dye. Pigment. 103, 50–54.
- Khan, S.A., Ahmad, A., Khan, M.I., Yusuf, M., Shahid, M., Manzoor, N., Mohammad, F., 2012. Antimicrobial activity of wool yarn dyed with Rheum emodi L. (Indian Rhubarb). Dye. Pigment. 95, 206–214.
- Kim, T.-K., Yoon, S.-H., Son, Y.-A., 2004. Effect of reactive anionic agent on dyeing of

cellulosic fibers with a Berberine colorant. Dye. Pigment. 60, 121–127.

- Křížová, H., Wiener, J., 2016. Comparison of UV protective properties of woollen fabrics dyed with yellow natural dyes from different plant sources. Environ. Sci. 2, 2454–9916.
- Kumar, J.K., Sinha, A.K., 2004. Resurgence of natural colourants: a holistic view. Nat. Prod. Res. 18, 59–84.
- Lee, Y.-H., Hwang, E.-K., Kim, H.-D., 2009. Colorimetric assay and antibacterial activity of cotton, silk, and wool fabrics dyed with peony, pomegranate, clove, coptis chinenis and gallnut extracts. Materials (Basel). 2, 10–21.
- Lee, Y.-H., Kim, H.-D., 2004. Dyeing properties and colour fastness of cotton and silk fabrics dyed withCassia tora L. extract. Fibers Polym. 5, 303–308.
- Li, D., Sun-Waterhouse, D., Wang, Y., Qiao, X., Chen, Y., Li, F., 2019. Interactions of Some Common Flavonoid Antioxidants. Encycl. Food Chem. 644–649.
- Li, S., Lu, M., Hu, R., Tang, T., Hou, K., Liu, Y., 2019. Dyeing ramie fabrics with curcumin in NaOH/urea solution at low temperature. Cloth. Text. Res. J. 37, 66–79.
- Maamoun, D., Salem, A.A., Marie, M.M., 2007. A new approach in printing polyamide 6 fabrics with natural dyes. Studies 14, 17.
- Mansour, R., 2018. Natural dyes and pigments: Extraction and applications. Handb. Renew. Mater. Color. Finish. 75–102.
- Mantzouris, D., Karapanagiotis, I., 2014. Identification of indirubin and monobromoindirubins in Murex brandaris. Dye. Pigment. 104, 194–196.
- Markham, K.R., 1982. Techniques of flavonoid identification., 1st ed, Techniques of flavonoid identification. Academic press, London.
- Maulik, S.R., Das, D., Bhattacharya, S.C., 2011. Modification of cotton fabric with acrylamide in the presence of K2S2O8 for improving dyeability of natural dyes. J. Text. Inst. 102, 131–139.
- Mongkholrattanasit, R., Cholachatpinyo, A., Tubtimthai, N., Rungruangkitkrai, N., 2014. An evaluation of UV protection imparted by wool fabric dyed with natural dye from

eucalyptus leaf. Chiang Mai J. Sci 41, 1208–1219.

- Mongkholrattanasit, R., Kryštůfek, J., Wiener, J., 2009. Dyeing of Wool and Silk by Eucalyptus Leaves Extract. J. Nat. Fibers 6, 319–330.
- Mulec, I., Gorjanc, M., 2015. The Influence of Mordanting on the Dyeability of Cotton Dyed with Turmeric Extract. Tekstilec 58.
- Mumtaz, R., Bashir, S., Numan, M., Shinwari, Z.K., Ali, M., 2019. Pigments from soil bacteria and their therapeutic properties: A mini review. Curr. Microbiol. 76, 783–790.
- Mussak, R.A.M., Bechtold, T., 2009. Natural Colorants in Textile Dyeing, in: Handbook of Natural Colorants. John Wiley & Sons, Ltd, Chichester, UK, pp. 315–337.
- Naz, S., Bhatti, I.A., 2011. Dyeing properties of cotton fabric using un-irradiated and gamma irradiated extracts of Eucalyptus camaldulensis bark powder. Indian J. Fibre Text. Res. 36, 132–146.
- Nazari, A., 2017. Efficient mothproofing of wool through natural dyeing with walnut hull and henna against Dermestes maculatus. J. Text. Inst. 108, 755–765.
- Obara, H., Onodera, J., 1979. Structure of Carthamin. Chem. Lett. 8, 201-204.
- Oda, H., 2001. Improvement of the light fastness of natural dyes: the action of singlet oxygen quenchers on the photofading of red carthamin. Color. Technol. 117, 204–208.
- Omer, K.A., Tao, Z., Seedahmed, A.I., 2015. New approach for dyeing and UV protection properties of cotton fabric using natural dye extracted from henna leaves. Fibres Text. East. Eur. 23, 60-65.
- Pal, A., Tripathi, Y.C., Kumar, R., Upadhyay, L., 2016. Antibacterial efficacy of natural dye from Melia composita leaves and its application in sanitized and protective textiles. J. Pharm. Res. 10, 154–159.
- Patel, B.H., 2011. Natural dyes, in: Clark, M. (Ed.), Handbook of Textile and Industrial Dyeing; Principles, Processes and Types of Dyes. Woodhead Publishing, Cambridge, UK, pp. 395–424.
- Patil, P.D., Rao, C.R., Wasif, A.I., 2012. Revival of natural dyes: Smart use of biodiversity.

Colourage, Mag. Commun. P. Ltd. NCR-Delhi.

- Perez-Vizcaino, F., Fraga, C.G., 2018. Research trends in flavonoids and health. Arch. Biochem. Biophys. 646, 107–112.
- Pisitsak, P., Hutakamol, J., Jeenapak, S., Wanmanee, P., Nuammaiphum, J., Thongcharoen, R., 2016. Natural dyeing of cotton with Xylocarpus granatum bark extract: Dyeing, fastness, and ultraviolet protection properties. Fibers Polym. 17, 560–568.
- Prabhu, K.H., Teli, M.D., 2014. Eco-dyeing using Tamarindus indica L. seed coat tannin as a natural mordant for textiles with antibacterial activity. J. Saudi Chem. Soc. 18, 864–872.
- Pruthi, N., Chawla, G.D., Yadav, S., 2008. Dyeing of silk with barberry bark dye using mordant combination, 40-44.
- Purwar, S., 2016. Application of natural dye on synthetic fabrics: A review. Int. J. Home Sci. 2, 283–287.
- Rahman, N.A.A., Tajuddin, R., Tumin, S.M., 2013. Optimization of natural dyeing using ultrasonic method and biomordant. Int. J. Chem. Eng. Appl. 4, 161.
- Rattanaphani, S., Chairat, M., Bremner, J.B., Rattanaphani, V., 2007. An adsorption and thermodynamic study of lac dyeing on cotton pretreated with chitosan. Dye. Pigment. 72, 88–96.
- Rehman, F., Sanbhal, N., Naveed, T., Farooq, A., Wang, Y., Wei, W., 2018. Antibacterial performance of Tencel fabric dyed with pomegranate peel extracted via ultrasonic method. Cellulose 25, 4251–4260.
- Rekaby, M., Salem, A.A., Nassar, S.H., 2009. Eco-friendly printing of natural fabrics using natural dyes from alkanet and rhubarb. J. Text. Inst. 100, 486–495.
- Rimpi, Archana, S., 2017. Protection and application of natural mosquito repellents cotton fabric through dyeing. Int. J. Innov. Res. Multidiscip. F. 3.
- Rovira, J., Nadal, M., Schuhmacher, M., Domingo, J.L., 2015. Human exposure to trace elements through the skin by direct contact with clothing: Risk assessment. Environ. Res. 140, 308–316.

- Rungruangkitkrai, N., Mongkholrattanasit, R., 2012. Eco-Friendly of Textiles Dyeing and Printing with Natural Dyes Nattadon Rungruangkitkrai1, Rattanaphol Mongkholrattanasit2, b.
- Salah, S.M., 2013. Antibacterial activity and ultraviolet (UV) protection property of some Egyptian cotton fabrics treated with aqueous extract from banana peel. African J. Agric. Res. 8, 3994–4000.
- Samanta, A.K., 2018. Application of Natural Dyes to Cotton and Jute Textiles: Science and Technology and Environmental Issues. Handb. Renew. Mater. Color. Finish. 213–277.
- Samanta, A.K., Agarwal, P., 2009. Application of natural dyes on textiles, 384-399.
- Samanta, A.K., Agarwal, P., 2007. Dyeing of jute and cotton fabrics using jackfruit wood extract: Part I—Effects of mordanting and dyeing process variables on colour yield and colour fastness properties, 466-476.
- Samanta, A.K., Agarwal, P., Datta, S., 2008. Physico-chemical studies on dyeing of jute and cotton fabrics using jackfruit wood extract: Part II—Dyeing kinetics and thermodynamic studies, 66-72.
- Samanta, A.K., Agarwal, P., Datta, S., 2006. Physico-chemical studies on dyeing of jute textiles with natural dye extracted from red sandalwood. J. Inst. Eng. (India)—Textile Eng. 87, 16–26.
- Samanta, A.K., Konar, A., 2011. Dyeing of textiles with natural dyes. Nat. Dye. 3.
- Samanta, A.K., Konar, A., Datta, S., 2012. Dyeing of jute fabric with tesu extract: Part II– Thermodynamic parameters and kinetics of dyeing.
- Samanta, A.K., Mukhopadhyay, A., Konar, A., Shome, D., Kar, T.R., 2016. Dyeability of chemically modified cotton muslin fabric using natural amino acid extract from soya bean seed. J. Text. Res. 86, 2179–2192.
- Samanta, A.K., Singhee, D., Sengupta, A., Rahim, S.A., 2003. Application of selective natural dyes on jute and cotton fabrics by different techniques. J. Inst. Eng. (India)— Textile Engg 83, 22–33.

- Samanta, P., Singhee, D., Samanta, A.K., 2018. Fundamentals of natural dyeing of textiles: pros and cons. Curr. Trends Fash. Technol. Text. Eng. 2, 1–8.
- Sarkar, A.K., Seal, C.M., 2003. Color strength and colorfastness of flax fabrics dyed with natural colorants. Cloth. Text. Res. J. 21, 162–166.
- Savvidis, G., Karanikas, E., Nikolaidis, N., Eleftheriadis, I., Tsatsaroni, E., 2014. Ink-jet printing of cotton with natural dyes. Color. Technol. 130, 200–204.
- Savvidis, G., Karanikas, V., Zarkogianni, M., Eleftheriadis, I., Nikolaidis, N., Tsatsaroni, E., 2017. Screen-Printing of Cotton with Natural Pigments: Evaluation of Color and Fastness Properties of the Prints. J. Nat. Fibers 14, 326–334.
- Saxena, S., Raja, A.S.M., 2014. Natural dyes: sources, chemistry, application and sustainability issues, in: Roadmap to Sustainable Textiles and Clothing. Springer, pp. 37–80.
- Schweppe, H., 1993. Handbuch der Naturfarbstoffe : Vorkommen, Verwendung, Nachweis. Nikol Verlag, Landsberg/Lech, Germany.
- Sekar, N., 1999. Application of natural colourants to textiles principles and limitation. Colourage 46, 33–34.
- Sen, T., Barrow, C.J., Deshmukh, S.K., 2019. Microbial pigments in the food industry— Challenges and the way forward. Front. Nutr. 6, 7.
- Senthilkumar, P., Umashankar, P., Sujatha, B., 2002. Ultrasonic dyeing of cotton fabrics with neem leaves. Indian Text. J. 112, 15–18.
- Shahid-ul-Islam, B.S. Butola, A.R., 2018. Chitosan polysaccharide as a renewable functional agent to develop antibacterial, antioxidant activity and colourful shades on wool dyed with tea extract polyphenols. Int. J. Biol. Macromol. 120, 1999–2006.
- Shahid-ul-Islam, Rather, L.J., Shabbir, M., Sheikh, J., Bukhari, M.N., Khan, M.A., Mohammad, F., 2019. Exploiting the potential of polyphenolic biomordants in environmentally friendly coloration of wool with natural dye from *Butea monosperma* flower extract. J. Nat. Fibers 16, 512–523.

- Shahid, M., Mohammad, F., 2013. Perspectives for natural product based agents derived from industrial plants in textile applications–a review. J. Clean. Prod. 57, 2–18.
- Shahid, M., Shahid-ul-Islam, Mohammad, F., 2013. Recent advancements in natural dye applications: a review. J. Clean. Prod. 53, 310–331.
- Shakyawar, D.B., Raja, A.S.M., Kumar, A., Pareek, P.K., 2015. Antimoth finishing treatment for woollens using tannin containing natural dyes. Indian J. Fibre Text. Res. 40, 200– 202.
- Shanker, R., Vankar, P.S., 2007. Dyeing cotton, wool and silk with Hibiscus mutabilis (Gulzuba). Dye. Pigment. 74, 464–469.
- Singh, P., 2020. Application of Acacia Catechu Natural Dye on Banana Fiber. Ergon. Int. J. 4.
- Singh, R., Jain, A., Panwar, S., Gupta, D., Khare, S.K., 2005. Antimicrobial activity of some natural dyes. Dye. Pigment. 66, 99–102.
- Sriumaoum, V., Sodsangchan, C., Setthayanond, J., Suwanruji, P., Tooptompong, P., 2014. Effect of chitosan and turmeric dye on ultraviolet protection properties of polyester fabric, in: Applied Mechanics and Materials. Trans Tech Publ, pp. 658–661.
- Syamili, E., Elayarajah, B., Rajendran, R., Venkatrajah, B., Kumar, P.A., 2012. Antibacterial cotton finish using green tea leaf extracts interacted with copper. Asian J. Text. 2, 6.
- Taha, M.A., Osman, H., Bakr, M.M., Ibrahim, H.M., 2020. Novel green printing of cotton, wool and polyester fabrics with natural alkanet dye nanoparticles. Eur. J. Mol. Clin. Med. 7, 1609–1623.
- Teli, M.D., Pandit, P., 2018. A novel natural source Sterculia foetida fruit shell waste as colorant and ultraviolet protection for linen. J. Nat. Fibers 15, 337–343.
- Teli, M.D., Paul, R., Pardeshi, P.D., 2001. Natural dyes: Classification, chemistry and extraction methods. Part II: Classification, environmental aspects and fastness properties, Colourage.
- Teli, M.D., Paul, R., Pardeshi, P.D., 2000. Natural dyes: Classification, chemistry and

extraction methods. Part- I: Chemical classes, extraction methods and future prospects, Colourage.

- Teli, M.D., Sheikh, J., Shastrakar, P., 2013. Exploratory investigation of chitosan as mordant for eco-friendly antibacterial printing of cotton with natural dyes. J. Text. 2013, 1-6.
- Ticha, M. Ben, Haddar, W., Meksi, N., Guesmi, A., Mhenni, M.F., 2016. Improving dyeability of modified cotton fabrics by the natural aqueous extract from red cabbage using ultrasonic energy. Carbohydr. Polym. 154, 287–295.
- Vaidyanathan, J., Bhathena-Langdana, Z., Adivarekar, R. V, Nerurkar, M., 2012. Production, partial characterization, and use of a red biochrome produced by Serratia sakuensis subsp. nov strain KRED for dyeing natural fibers. Appl. Biochem. Biotechnol. 166, 321–335.
- Vankar, Padma Shree, 2017. Natural dyes for textiles : sources, chemistry and applications, First. ed. The Textile Institute and Woodhead Publishing, Manchester, England.
- Vankar, P S, 2017. Structure-mordant interaction, replacement by biomordants and enzymes. Nat. Dye. Text. Sources, Chem. Appl. 89–102.
- Vankar, P.S., 2000. Chemistry of natural dyes. Resonance 5, 73-80.
- Vankar, P.S., Shanker, R., 2009. Eco-friendly pretreatment of silk fabric for dyeing with Delonix regia extract. Color. Technol. 125, 155–160.
- Vankar, P.S., Shanker, R., 2008. Ecofriendly ultrasonic natural dyeing of cotton fabric with enzyme pretreatments. Desalination 230, 62–69.
- Vankar, P.S., Shanker, R., Dixit, S., Mahanta, D., Tiwari, S.C., 2008a. Sonicator dyeing of natural polymers with Symplocos spicata by metal chelation. Fibers Polym. 9, 121.
- Vankar, P.S., Shanker, R., Dixit, S., Mahanta, D., Tiwari, S.C., 2008b. Sonicator dyeing of modified cotton, wool and silk with Mahonia napaulensis DC. and identification of the colorant in Mahonia. Ind. Crops Prod. 27, 371–379.
- Vankar, P.S., Shanker, R., Srivastava, J., 2007. Ultrasonic dyeing of cotton fabric with aqueous extract of Eclipta alba. Dye. Pigment. 72, 33–37.

- Vasileiadou, A., Karapanagiotis, I., Zotou, A., 2019. UV-induced degradation of wool and silk dyed with shellfish purple. Dye. Pigment. 168, 317–326.
- Vasileiadou, A., Karapanagiotis, I., Zotou, A., 2016. Determination of Tyrian purple by high performance liquid chromatography with diode array detection. J. Chromatogr. A 1448, 67–72.
- Velmurugan, P., Chae, J., Lakshmanaperumalsamy, P., Yun, B., Lee, K., Oh, B., 2009. Assessment of the dyeing properties of pigments from five fungi and anti-bacterial activity of dyed cotton fabric and leather. Color. Technol. 125, 334–341.
- Velmurugan, P., Kim, M.-J., Park, J.-S., Karthikeyan, K., Lakshmanaperumalsamy, P., Lee, K.-J., Park, Y.-J., Oh, B.-T., 2010. Dyeing of cotton yarn with five water soluble fungal pigments obtained from five fungi. Fibers Polym. 11, 598–605.
- Vijaykumar, A. V, Kumar, R.K., 1999. Colors from common weeds., in: Book of Papers of the Convention on Natural Dyes. Department of Textile Technology, IIT Delhi, New Delhi, pp. 9–11.
- Wang, L., Li, J., Feng, H., 2009. Dyeing of flax fabric with natural dye from chestnut shells. Pigment Resin Technol. 38, 347-352.
- Wätjen, W., Michels, G., Steffan, B., Niering, P., Chovolou, Y., Kampkötter, A., Tran-Thi, Q.-H., Proksch, P., Kahl, R., 2005. Low Concentrations of Flavonoids Are Protective in Rat H4IIE Cells Whereas High Concentrations Cause DNA Damage and Apoptosis. J. Nutr. 135, 525–531.
- Weber, G., Chen, H., Hinsch, E., Freitas, S., Robinson, S., 2014. Pigments extracted from the wood-staining fungi Chlorociboria aeruginosa, Scytalidium cuboideum, and S. ganodermophthorum show potential for use as textile dyes. Color. Technol. 130, 445– 452.
- Yadav, P., Sharma, E., Fatima, N., 2010. Printing of silk with natural red cabbage dye 53, 36–40.
- Yang, T.-T., Guan, J.-P., Chen, G., Tang, R.-C., 2018. Instrumental characterization and functional assessment of the two-color silk fabric coated by the extract from Dioscorea

cirrhosa tuber and mordanted by iron salt-containing mud. Ind. Crops Prod. 111, 117–125.

- Yıldırım, F.F., Yavas, A., Avinc, O., 2020. Printing with sustainable natural dyes and pigments. Sustain. Text. Appar. Ind. Process Sustain. 1–35.
- Yusuf, M., Mohammad, F., Shabbir, M., 2017a. Eco-friendly and effective dyeing of wool with anthraquinone colorants extracted from Rubia cordifolia roots: Optimization, colorimetric and fastness assay. J. King Saud Univ. 29, 137–144.
- Yusuf, M., Shabbir, M., Mohammad, F., 2017b. Natural Colorants: Historical, Processing and Sustainable Prospects. Nat. Products Bioprospect. 7, 123–145.
- Yusuf, M., Shahid, M., Khan, M.I., Khan, S.A., Khan, M.A., Mohammad, F., 2015. Dyeing studies with henna and madder: A research on effect of tin (II) chloride mordant. J. Saudi Chem. Soc. 19, 64–72.
- Zerin, I., Farzana, N., Muhammad Sayem, A., Anang, D.M., Haider, J., 2019. Potentials of Natural Dyes for Textile Applications. 2, 873-883.
- Zhang, R., Wang, A., 2015. Modification of wool by air plasma and enzymes as a cleaner and environmentally friendly process. J. Clean. Prod. 87, 961–965.
- Zheng, G.H., Fu, H. Bin, Liu, G.P., 2011. Application of rare earth as mordant for the dyeing of ramie fabrics with natural dyes. Korean J. Chem. Eng. 28, 2148–2155.
- Zhou, Y., Tang, R.-C., 2016. Modification of curcumin with a reactive UV absorber and its dyeing and functional properties for silk. Dye. Pigment. 134, 203–211.
- Zuber, M., Adeel, S., Rehman, F.-U., Anjum, F., Muneer, M., Abdullah, M., Zia, K.M., 2019. Influence of microwave radiation on dyeing of bio-mordanted silk fabric using neem bark (Azadirachta indica)-based tannin natural dye. J. Nat. Fibers. 17, 1410-1422.